

Table #1 Values used in program to pull the glass needles.					
	Heat	Pull	Velocity	Time	
Step 1	780	25	5	250	
Step 2	780	40	10	250	
Step 3	780	10	5	250	
Step 4	790	10	10	250	
Step 5	780	0	23	250	