

Journal of Visualized Experiments

Synthesis and Characterization of Amphiphilic Gold Nanoparticles

--Manuscript Draft--

Article Type:	Invited Methods Article - JoVE Produced Video
Manuscript Number:	JoVE58872R1
Full Title:	Synthesis and Characterization of Amphiphilic Gold Nanoparticles
Keywords:	amphiphilic gold nanoparticles; sulfonated ligands; synthesis; characterization; binary ligand coating; self-assembled monolayer
Corresponding Author:	Francesco Stellacci Ecole Polytechnique Federale de Lausanne Lausanne, VD SWITZERLAND
Corresponding Author's Institution:	Ecole Polytechnique Federale de Lausanne
Corresponding Author E-Mail:	francesco.stellacci@epfl.ch
Order of Authors:	Francesco Stellacci Zekiye P Guven Paulo H Jacob Silva Zhi Luo Urszula B Cendrowska Matteo Gasbarri Samuel T Jones
Additional Information:	
Question	Response
Please indicate whether this article will be Standard Access or Open Access.	Standard Access (US\$2,400)
Please indicate the city, state/province, and country where this article will be filmed . Please do not use abbreviations.	Lausanne, VD, Switzerland

EIDGENÖSSISCHE TECHNISCHE HOCHSCHULE LAUSANNE
POLITECNICO FEDERALE DI LOSANNA
SWISS FEDERAL INSTITUTE OF TECHNOLOGY LAUSANNE

Institute of Materials
Interfaculty Institute of Bioengineering
Supramolecular NanoMaterials and Interfaces Laboratory



Francesco Stellacci
Constellium Chair Professor
Director of the Integrative Food and Nutrition Center


31 July 2018

Dear Benjamin:

Following your invitation we are hereby submitting a paper entitled "Synthesis and Characterization of Amphiphilic Gold Nanoparticles" for consideration as an Article in JOVE.

This paper describes in detail the synthesis, purification, and characterization of some key nanoparticles that we have been synthesising since 2004.

On behalf of all of the authors,



Francesco Stellacci
Constellium Chair Professor
Director, Integrative Food and Nutrition Center

As recommended referees we suggest

1. Prof. Fabrizio Mancin
University of Padua
fabrizio.mancin@unipd.it
2. Prof. Xiaogang Liu
National University of Singapore
chmx@nus.edu.sg
3. Prof. Amala Dass
University of Mississippi
amal@olemiss.edu
4. Prof. Jill Millstone
University of Pittsburgh
jem210@pitt.edu
5. Prof. Bartosz A. Grzybowski
Ulsan National Institute of Science and Technology
nanogrzybowski@gmail.com
grzybor72@unist.ac.kr
6. Prof. Laura Fabris
Rutgers University
lfabris@rci.rutgers.edu

TITLE:**Synthesis and Characterization of Amphiphilic Gold Nanoparticles****AUTHORS & AFFILIATIONS:**

Zekiye P. Guven¹ *, Paulo H. Jacob Silva¹ *, Zhi Luo¹, Urszula B. Cendrowska¹, Matteo Gasbarri¹, Samuel T. Jones^{1,2}, Francesco Stellacci^{1,3}

¹Institute of Materials, École Polytechnique Fédérale de Lausanne, Lausanne, Switzerland

²School of Materials, University of Manchester, Manchester, United Kingdom

³Interfaculty Institute of Bioengineering, École Polytechnique Fédérale de Lausanne, Lausanne, Switzerland

* These authors contributed equally.

Corresponding Author:

Francesco Stellacci (francesco.stellacci@epfl.ch)

Tel: +41-21-693-7872

E-mail Addresses of the Co-authors:

Zekiye P. Guven (zekiye.guven@epfl.ch)

Paulo H. Jacob Silva (pjacob@alum.mit.edu)

Zhi Luo (zhi.luo@epfl.ch)

Urszula B. Cendrowska (urszula.cendrowska@epfl.ch)

Matteo Gasbarri (matteo.gasbarri@epfl.ch)

Samuel T. Jones (samuel.jones-4@manchester.ac.uk)

KEYWORDS:

amphiphilic gold nanoparticles, sulfonated ligands, synthesis, characterization, binary ligand coating, self-assembled monolayer

SUMMARY:

Amphiphilic gold nanoparticles can be used in many biological applications. A protocol to synthesize gold nanoparticles coated by a binary mixture of ligands and a detailed characterization of these particles is presented.

ABSTRACT:

Gold nanoparticles covered with a mixture of 1-octanethiol (OT) and 11-mercapto-1-undecane sulfonic acid (MUS) have been extensively studied because of their interactions with cell membranes, lipid bilayers, and viruses. The hydrophilic ligands make these particles colloidally stable in aqueous solutions and the combination with hydrophobic ligands creates an amphiphilic particle that can be loaded with hydrophobic drugs, fuse with the lipid membranes, and resist nonspecific protein adsorption. Many of these properties depend on nanoparticle size and the composition of the ligand shell. It is, therefore, crucial to have a reproducible synthetic method and reliable characterization techniques that allow the determination of nanoparticle properties

and the ligand shell composition. Here, a one-phase chemical reduction, followed by a thorough purification to synthesize these nanoparticles with diameters below 5 nm, is presented. The ratio between the two ligands on the surface of the nanoparticle can be tuned through their stoichiometric ratio used during synthesis. We demonstrate how various routine techniques, such as transmission electron microscopy (TEM), nuclear magnetic resonance (NMR), thermogravimetric analysis (TGA), and ultraviolet-visible (UV-Vis) spectrometry, are combined to comprehensively characterize the physicochemical parameters of the nanoparticles.

INTRODUCTION:

The ligand shell of gold nanoparticles can be engineered to exhibit several different properties that can be applied to address challenges in biomedicine¹⁻⁴. Such versatility allows for the control of the intermolecular interactions between nanoparticles and biomolecules⁵⁻⁷. Hydrophobicity and charge play a decisive role, as well as other surface parameters that affect how nanoparticles interact with biomolecules^{5,8,9}. To tune the nanoparticles' surface properties, the choice of thiolate molecules that make up the ligand shell offers a myriad of possibilities, according to the characteristics sought. For example, a mixture of ligand molecules with hydrophobic and hydrophilic (*e.g.*, charged) end groups are often used to generate amphiphilic nanoparticles^{10,11}.

One prominent example of this type of nanoparticles is protected by a mixture of OT and MUS (hereafter called MUS:OT nanoparticles) that has been shown to possess many relevant properties¹²⁻¹⁴. First, with a ligand shell composition of 66% MUS (hereafter 66:34 MUS:OT), the colloidal stability of the nanoparticles is high, reaching up to 33% in weight in deionized water, as well as in phosphate-buffered saline (1x, 4 mM phosphate, 150 mM NaCl)¹⁵. Moreover, these particles do not precipitate at relatively low pH values: for example, at pH 2.3 and with salt concentrations of 1 M NaCl¹⁵, these nanoparticles remain colloidally stable for months. The stoichiometric ratio between the two molecules on the ligand shell is important because it dictates the colloidal stability in solutions with a high ionic strength¹⁶.

These particles have been shown to traverse the cell membrane without porating it, *via* an energy-independent pathway^{1,12}. The spontaneous fusion between these particles and lipid bilayers underlies their diffusivity through cell membranes¹⁷. The mechanism behind this interaction is the minimization of contact between a hydrophobic solvent-accessible surface area and water molecules upon fusion with lipid bilayers¹⁸. Compared to all-MUS nanoparticles (nanoparticles having only the MUS ligand on their shell), the higher hydrophobicity on mixed MUS:OT nanoparticles (for example, at a 66:34 MUS:OT composition) increases the span of the core diameter that can fuse with lipid bilayers¹⁸. Different self-assembly organizations of the ligand shell correlate to distinct binding modes of 66:34 MUS:OT nanoparticles with various proteins, such as albumin and ubiquitin, when compared to all-MUS particles¹⁹. Recently, it has been reported that 66:34 MUS:OT nanoparticles can be utilized as a broad-spectrum antiviral agent that irreversibly destroys the viruses because of multivalent electrostatic bindings of MUS ligands and nonlocal couplings of OT ligands to capsid proteins¹⁴. In all these cases, it has been found that the hydrophobic content, as well as the core size of the nanoparticles, determines how these bio-nano interactions take place. These diverse properties of MUS:OT nanoparticles have prompted many computer simulation studies that aimed to clarify the mechanisms

underpinning the interactions between MUS:OT particles and various biological structures such as lipid bilayers²⁰.

The preparation of MUS:OT-protected Au nanoparticles poses a few challenges. First, the charged ligand (MUS) and the hydrophobic ligand (OT) are immiscible. Thus, the solubility of the nanoparticles and of the ligands needs to be taken into account throughout the synthesis, as well as during characterization. Additionally, the purity of the MUS ligand molecules—specifically, the content of inorganic salts in the starting material—influences the quality, reproducibility, as well as the short- and long-term colloidal stability of the nanoparticles.

Here, a detailed synthesis and characterization of this class of amphiphilic gold nanoparticles protected by a mixture of MUS and OT are outlined. A protocol for the synthesis of the negatively charged MUS ligand is reported to ensure the purity and, hence, the reproducibility of different nanoparticle syntheses. Then, the procedure to generate these nanoparticles, based on a common one-phase synthesis, followed by thorough purification, is reported in detail. Various necessary characterization techniques²¹, such as TEM, UV-Vis, TGA, and NMR, have been combined to obtain all the necessary parameters for any further biological experiments.

PROTOCOL:

1. Synthesis of 11-mercapto-1-undecanesulfonate (MUS)

NOTE: This protocol can be used at any scale desired. Here, a 10 g scale-of-product is described.

1.1. Sodium undec-10-enesulfonate

1.1.1. Add 11-bromo-1-undecene (25 mL, 111.975 mmol), sodium sulfite (28.75 g, 227.92 mmol), and benzyltriethylammonium bromide (10 mg) to a mixture of 200 mL of methanol (MeOH) and 450 mL of deionized (DI) water (4:9 v/v MeOH:H₂O ratio) in a 1 L round-bottom flask.

1.1.2. Reflux the reaction mixture at 102 °C for 48 h. Cap the system with a pressure relief mechanism—for example, a balloon with a needle, or simply a needle. This reaction is not sensitive to atmospheric gases.

NOTE: The solution becomes colorless when the reaction is complete.

1.1.3. Connect the reaction mixture to a rotary evaporator to evaporate MeOH and reduce the volume to approximately 300 mL.

1.1.4. Transfer the remaining solution to a 1 L separatory funnel.

1.1.5. Extract the remaining aqueous solution 5x with diethyl ether, using the separatory funnel. Unreacted 11-bromo-1-undecene stays in the diethyl ether phase and the sulfonated product in H₂O.

CAUTION: Release any pressure buildup frequently during the extraction, and consult the correct usage of separatory funnels.

1.1.6. Collect the final extracted water solution into a 1 L single-neck round-bottom flask.

1.1.7. Connect the reaction flask to a rotary evaporator by putting a bit of grease (or Teflon ring strips or any other sealant) between the flask and the trap.

1.1.8. Decrease the vacuum slowly to evaporate the aqueous phase in a rotary evaporator. Because the product is a surfactant, foaming will occur during the evaporation. To circumvent this problem, follow the instruction in the next step.

1.1.8.1. Add ethanol to the mixture to accelerate the evaporation of H₂O and prevent foaming. When foaming restarts because of the decrease in ethanol content, stop the evaporation, remove the flask from the rotary evaporator, add more ethanol (about one-third of the total volume), and reconnect the flask to the rotary evaporator. Repeat this process until the solution mixture decreases significantly and does not form bubbles.

1.1.9. Dry the white powder directly by connecting the flask to a high vacuum. The drier the powder, the less inorganic salts will creep into the subsequent steps.

NOTE: Heat can be used to dry the product—for example, by keeping the flask under vacuum in a 60 °C bath and left overnight.

1.1.10. Suspend the white powder in 400 mL of methanol in a flask. Sonicate to dissolve the maximum amount of product.

NOTE: The goal of this step is to dissolve the product but not the inorganic byproducts, such as excess sodium sulfite and sodium bromide, that have limited solubility in methanol. Use methanol with the lowest water content possible, because water in the methanol will increase the solubility of the inorganic byproducts in the solvent.

1.1.11. To increase the solubility of the product, methanol can be gently heated close to its boiling point (~64 °C).

CAUTION: Make sure to work under a fume hood during the heating of the flask. The fumes of the evaporated methanol are dangerous.

1.1.12. Filter the solution to remove the methanol insoluble inorganic byproducts. Use a filtering flask connected to a vacuum pump and a filtering funnel with quantitative filter paper, or a borosilicate filter. Both the product and the inorganic salts are white powders when dry: the product is soluble in methanol, while the salts are not.

1.1.13. Transfer the filtered solution from the filtering flask to a 1 L round-bottom flask.

1.1.14. Connect the flask to a rotary evaporator and evaporate the methanolic solution at 45 °C, redissolve the white powder in methanol, and filter the solution (protocol steps 1.1.7, 1.1.8, and 1.1.9). Repeat this process at least 2x, to decrease the amount of inorganic salt.

1.1.15. Collect the white, methanol soluble powder (approximately 30 g, at this scale).

1.1.16. Dissolve approximately 10 mg of product in 500 µL of D₂O and transfer the solution to an NMR tube.

1.1.17. Perform ¹H NMR spectrometry on the product in D₂O at 400 MHz with 32 scans.

NOTE: The peak assignments for ¹H NMR (D₂O) are 5.97 (m, 1H), 5.09 (m, 2H), 2.95 (t, 2H), 2.10 (m, 2H), 1.77 (q, 2H), 1.44 (br s, 12H).

1.2. Sodium 11-acetylthio-undecanesulfonate

1.2.1. Dissolve the approximate 30 g of sodium undec-10-enesulfonate (the reaction product of section 1.1) in 500 mL of methanol inside a 1 L round-bottom flask. Add a 2.6x excess of thioacetic acid to the solution and stir it in front of a UV lamp (250 W) overnight (~12 h). In case a UV lamp is not available, the reaction can be performed by refluxing using a radical initiator, such as azobisisobutyronitrile (AIBN); however, the use of a UV lamp is strongly recommended.

CAUTION: Make sure to work under the fume hood at all times. If the flask needs to be transported to another space where the UV lamp is located, seal the flask to avoid spreading the strong odor of thioacetic acid. Exercise care when operating a UV lamp: completely block the space where the lamp is located and consult the institution's safety guidelines on how to operate a UV lamp.

1.2.2. Monitor the reaction by taking ~2 mL aliquots from the reaction, evaporate solvent, and add deuterated water to check with ¹H NMR. Once the peaks corresponding to the double bond disappear, stop the reaction.

NOTE: Usually, after 12 h in front of the UV lamp, the reaction is complete. If the reaction mixture becomes turbid, add more MeOH and continue the exposure to the UV light for six additional hours.

1.2.3. Evaporate all of MeOH in a rotary evaporator until the solid residue becomes orange-red. If left long enough, the product becomes brown to black.

CAUTION: Work mindfully because of the strong odors from the thioacetic acid. The strong odors of any thiolate spills can be neutralized using an aqueous solution of bleach (sodium hypochlorite).

1.2.4. Using a filtering flask, wash the product with diethyl ether to remove any excess thioacetic acid, until no more colored (orange-yellow) substances appear in the diethyl ether supernatant. Dry the solid under high vacuum and, then, dissolve it in methanol, yielding a yellow to orange solution.

NOTE: The color may vary at this step.

1.2.5. Add 3 g of carbon black to the solution, mix vigorously, and filter the mixture through filtration medium (see **Table of Materials**) covering two-thirds of a fluted filter paper.

NOTE: The porous structure of carbon black captures the colored side-product material (and some of the product). The filtered solution should be clear. If the filtered solution is still colored (yellow), repeat this process.

1.2.6. Evaporate the solvent completely in a rotary evaporator and collect approximately 35 g of white powder.

1.2.7. Dissolve ~10 mg of the product in ~500 μL of D_2O and transfer the solution to NMR tubes.

1.2.8. Perform ^1H NMR on the product in D_2O at 400 MHz with 32 scans.

NOTE: The peak assignments for the ^1H NMR (D_2O) are 2.93 (t, 4H), 2.40 (s, 3H), 1.77 (m, 2H), 1.62 (m, 2H), 1.45 (br s, 14H).

1.3. MUS

1.3.1. Reflux sodium 11-acetylthio-undecanesulfonate at 102 $^\circ\text{C}$ in 400 mL of 1 M HCl for 12 h to cleave the thioacetate group and obtain a thiol.

1.3.2. Transfer the product to a 1.5 L or 2 L round-bottom flask. Add 200 mL of 1 M NaOH to the final solution and top it with 400 mL of DI water to have a final volume of 1 L. This will keep the solution acidic and prevent the crystallization of inorganic salts as product.

NOTE: A complete neutralization of the solution to pH 7 will result in the crystallization of a product insoluble in methanol.

1.3.3. Keep the clear solution at 4 $^\circ\text{C}$ and it will crystallize overnight. This step yields a pure product. The product crystallizes as fine crystals that are viscous when wet.

NOTE: To accelerate the crystallization, add presynthesized MUS to the solution, if available.

1.3.4. Decant the clear supernatant and centrifuge down the viscous white product in 50 mL centrifuge tubes for 5 min at 4,000 $\times g$.

1.3.5. Decant the supernatant into another flask and dry the white pellets under high vacuum—depending on the centrifuge available, this can be 2 - 16 tubes or more.

NOTE: Filtering is not advised because of the surfactant nature of the product; excessive foaming will occur and most of the product will be lost.

1.3.6. Collect approximately 12 g (about 30% yield) of methanol-soluble MUS from this purification step.

NOTE: Be mindful that the powder is fine and electrostatic—it tends to stick to spatulas and the surfaces of containers. Also, more material can be extracted from the supernatant of the centrifugation step by reducing the volume (to about a third of its original value) and keeping it at 4 °C. Decrease the volume even more (by 75%) to increase the yield at this step.

1.3.7. Dissolve ~10 mg of the product in ~500 µL of D₂O and transfer the solution to NMR tubes.

1.3.8. Perform ¹H NMR on the product in D₂O at 400 MHz with 32 scans.

NOTE: The peak assignments of ¹H NMR (D₂O) are 2.93 (t, 4H), 2.59 (t, 3H), 1.78 (m, 2H), 1.65 (m, 2H), 1.44 (br s, 14H). The calculated molar mass (including the sodium counterion) of the product is 290.42 g/mol.

2. Nanoparticle Synthesis: Preparation of the Reagents

2.1. Clean all glassware (one 250 mL and one 500 mL single-neck round-bottom flask, a 125 mL separatory funnel, and a small funnel) with fresh *aqua regia* (three parts hydrochloric acid to one part nitric acid). Rinse the glassware with an excess amount of water inside a fume hood and remove all the fumes. Then, rinse the glassware with ethanol and dry it in a laboratory glassware oven (40 - 60 °C is recommended).

2.2. Weigh 152.9 mg (0.45 mmol) of gold (III) chloride trihydrate (HAuCl₄·H₂O) in a small glass vial (10 or 20 mL clean glass vials, or on weighing paper).

2.3. Weigh 87 mg (0.3 mmol) MUS in a glass vial of 20 mL.

2.4. Add 10 mL of methanol to dissolve the MUS. Sonicate it in an ultrasonic bath until no solid material is visible, to ensure complete dissolution.

NOTE: Alternatively, using a heat gun or a warm bath (~60 °C), heat the solution gently. When heated, run cold water through the outside of the flask to bring it back to room temperature.

2.5. Add 26 µL (0.15 mmol) of OT to the methanol solution and agitate it to mix the ligands.

2.6. Weigh 500 mg (13 mmol) of sodium borohydride (NaBH_4) and add it to 100 mL of ethanol in the 250 mL round-bottom flask. Stir vigorously using magnetic stirring (600 - 800 rpm). (The NaBH_4 takes 10 to 20 min, depending on the grade, to form a clear solution in ethanol.)

3. Synthesis of Gold Nanoparticles

3.1. Dissolve gold salt in 100 mL of ethanol in the 500 mL round-bottom flask and start stirring at 800 rpm with a magnetic bar on a stirring plate. Make sure the gold salt dissolves completely.

3.2. Place a 100 mL separatory funnel above the round-bottom flask. Put a funnel on the top of the separatory funnel with a quantitative paper filter inside. When the NaBH_4 is dissolved in ethanol, start filtering the solution into the separatory funnel through the filter paper in the funnel.

3.3. Add the ligand solution to the reaction mixture. Wait 15 min for the formation of gold-thiolate complex. The color change of the reaction mixture from translucent yellow to turbid yellow indicates the formation of gold-thiolate complex.

3.4. Start adding the filtered NaBH_4 solution from the separatory funnel dropwise. Adjust the interval time of the drops so that the addition of NaBH_4 takes about 1 h.

3.5. After the complete addition of NaBH_4 , remove the funnel. Keep stirring the reaction for another hour. At the end of the reaction, remove the magnetic stirring bar using a magnet placed on the outside of the flask.

3.6. Use a septum to close the flask and pierce a needle into the septum to release the H_2 gas that will evolve after the reaction.

3.7. Keep the reaction mixture inside a laboratory refrigerator (4 °C) to precipitate the nanoparticles overnight.

4. Workup of the Synthesis

4.1. Decant the supernatant ethanol to reduce the volume.

4.2. Transfer the remaining precipitant to 50 mL centrifuge tubes and centrifuge for 3 min at 4,000 x g.

4.3. Decant the supernatant, disperse the nanoparticles again with ethanol by vortexing, and centrifuge them again. Repeat this washing process 4x.

4.4. Dry the nanoparticles under vacuum to remove the residual ethanol.

4.5. To clean the nanoparticles from free hydrophilic ligands/molecules, dissolve the precipitates in 15 mL of DI water and transfer them to the centrifuge tubes with a filtration membrane of 30 kDa cutoff molecular weight. Dialysis is also amenable for this procedure.

4.6. Centrifuge these tubes for 5 min at 4,000 x *g* to concentrate the nanoparticle solution.

4.7. Add 15 mL of DI water to this solution and centrifuge to concentrate again. Repeat this cleaning process at least 10x.

NOTE: One indication that the water-soluble impurities have been removed is the absence of foaming when agitating the aqueous waste; after all, most of the impurities are disulfides of MUS with itself or with OT (this can be determined by collecting the material and performing ¹H NMR).

4.8. After the centrifugation, transfer the concentrated nanoparticles to a 15 mL centrifuge tube. To turn the nanoparticles into a manageable powder, either precipitate them in a solvent such as acetone or freeze-dry the remaining aqueous solution. When freeze-dried, the nanoparticles tend to form a loose powder that sticks to surfaces and may be difficult to manipulate.

5. Characterization of the Nanoparticles

5.1. Purity

5.1.1. To check whether the nanoparticles are free from unbound ligands, dissolve 5 mg of dry nanoparticles in 600 µL of D₂O and perform a ¹H NMR measurement of the particles. If there are no sharp peaks of the ligands, it means the nanoparticles are free from small organic molecules.

5.2. Ligand ratio

5.2.1. Prepare a 150 mg/mL methanol-d₄ solution of iodine. Add 600 µL of this solution to the ~5 mg of nanoparticles in a glass vial, to etch the nanoparticles.

5.2.2. Wrap the cap of the vial with paraffin film and sonicate it in an ultrasonic bath for 20 min. Transfer the solution to an NMR tube and acquire a ¹H NMR (400 MHz) spectrum with 32 scans.

5.3. Ligand density

5.3.1. Transfer 2 to 8 mg of nanoparticles to a TGA crucible. Choose a temperature range from 30 °C to 900 °C and a speed of 5 °C per minute under N₂ gas.

5.4. Size distribution

5.4.1. TEM

5.4.1.1. Prepare 0.1 mg/mL nanoparticle solution in DI water. Drop 5 μ L of the prepared solution onto the 400-mesh carbon-supported copper grid. Wait until it dries.

5.4.1.2. Transfer the grid in a TEM holder and insert it into the microscope. Acquire 5 - 10 images with a magnification of at least 64,000X, operated at 200 kV.

NOTE: To increase the contrast, an objective aperture of 20 nm can be inserted.

5.4.2. UV-Vis spectra

5.4.2.1. Prepare a 0.2 mg/mL nanoparticle solution in DI water.

5.4.2.2. Put the required amount of this solution in the quartz cuvette and scan from 200 nm to 700 nm.

REPRESENTATIVE RESULTS:

The reaction steps to synthesize MUS are shown in **Figure 1**. The ^1H NMR spectra of the product of each step are represented in **Figure 2**. The synthesis workflow of the binary MUS:OT amphiphilic gold nanoparticles is described in **Figure 3**. Following the synthesis, the workup of the nanoparticles consisted of washing the particles several times with ethanol and DI water. Prior to any characterization of nanoparticles, the cleanliness of the nanoparticles from unbound free ligands was monitored by ^1H NMR in D_2O , as shown in **Figure 4**. The size distribution of the nanoparticles was characterized by TEM (**Figure 5a,b**). Localized surface plasmon resonance absorption was measured by acquiring UV-Vis spectra (**Figure 5c**).

The ratio of the two ligands was determined by etching the gold core using iodine, acquiring the ^1H NMR, and calculating the relative amounts of each ligand using the integrated values. **Figure 6** shows the representative spectra, as well as the procedure of NMR peak assignments. To find the ligand ratio between MUS and OT, we calculated the integrals of the peaks between 0.8 - 1 (I_1), 1.12 - 1.55 (I_2), 1.6 - 1.9 (I_3), and 2.6 - 3 (I_4) ppm. The I_1 peak contains signal from three OT hydrogens, the I_2 peak from a combination of 14 MUS hydrogens and 10 OT hydrogens, and the I_3 and I_4 peaks from four MUS hydrogens and two OT hydrogens (for each peak). Therefore, to find the OT percentage, it is necessary to normalize I_1 to 3 and apply the following expressions.

For I_2 ,

$$OT\% = \frac{1}{\left(\frac{I_2 - 10}{14}\right)} + 1$$

For I_3 and I_4 ,

$$OT\% = \frac{1}{\left(\frac{I_{3,4} - 2}{4}\right)} + 1$$

These calculations indicate the ratio of OT to MUS, assuming there is one arbitrary unit of OT in

the system. For **Figure 6B**, the three integrals gave similar values for OT percentage (*i.e.*, 15.3, 15.9, and 15.9 from I_2 , I_3 , and I_4 , respectively).

The surface coverage of the nanoparticles is examined by TGA as shown in **Figure 7**. TGA, NMR, and TEM data (**Figure 3**) are combined to calculate the ligand density, which is the number of ligands on a unit of surface area, approximating the particles to a sphere. (This calculation assumes that Na boils as NaHSO_3 .) TEM data shows that the average diameter of the nanoparticles is 2.4 nm, pointing to approximately 18.08 nm^2 ($A_{\text{par}} = 4\pi r^2$) of surface area (A_{par}) and 7.23 nm^3 ($V_{\text{par}} = 4\pi r^3/3$) of volume per particle (V_{par}). The density of gold is 19.9 g/cm^3 and the mass of one particle is $1.3969 \times 10^{-16} \text{ mg}$ ($\text{Mass}_{\text{particle}} = V_{\text{par}} \times \text{the density of gold} = 7.23 \text{ nm}^3 \times 19.9 \text{ g/cm}^3 \times 10^{-18} \text{ mm}^3/\text{nm}^3$). The remaining mass around 800°C corresponds to the gold core, and there are approximately 3.7×10^{16} particles (N_{par}) that are estimated using $N_{\text{par}} = (\text{Mass}_{\text{gold}}/\text{Mass}_{\text{particle}}) = 5.17 \text{ mg} / 1.3969 \times 10^{-16} \text{ mg}$. The total surface area (A_{tot}) of the particles is $6.69 \times 10^{17} \text{ nm}^2$ ($A_{\text{tot}} = N_{\text{par}} \times A_{\text{par}} = 3.69 \times 10^{16} \times 18.08 \text{ nm}^2$). The NMR of iodine-etched nanoparticles showed that the MUS:OT ratio is 85:15 and the amount of organic content in TGA is 0.00146 g. Therefore, there are 3.26×10^{18} ligands (N_{ligand}) following the formula of $N_{\text{ligand}} = [\text{Mass}_{\text{organic}} / ((R_{\text{OT}} \times M_{\text{wOT}}) + (R_{\text{MUS}} \times M_{\text{wMUS}})) / (R_{\text{MUS}} + R_{\text{OT}})] \times N_{\text{Avogadro}} = [0.00146 \text{ g} / ((15 \times 146 \text{ g/mol}) + (85 \times 267.42 \text{ g/mol})) / (85 + 15)] \times (6.02 \times 10^{23}) = 3.26 \times 10^{18}$. Finally, the ligand density is 4.8 ligands/nm^2 , calculated by dividing the N_{ligand} by A_{tot} ($4.8 = 3.26 \times 10^{18} / 6.69 \times 10^{17} \text{ nm}^2$). The stoichiometric ratios vs. the NMR ratios of the OT, resulting from various syntheses, are compared in **Figure 8**.

FIGURE AND TABLE LEGENDS:

Figure 1: Schematic of MUS synthesis. MUS synthesis is the key point for the reproducibility of amphiphilic nanoparticle synthesis. If MUS has a high salt content, the stoichiometric ratio of the ligands may deviate. $X = 9$.

Figure 2: NMR spectra of the molecules after each step in the MUS synthesis (400 MHz). (A) This panel shows the ^1H NMR spectrum of sodium undec-10-enesulfonate in D_2O . (B) This panel shows the ^1H NMR spectrum of sodium 11-acetylthio-undecanesulfonate in D_2O . (C) This panel shows the ^1H NMR spectrum of 11-mercapto-1-undecanesulfonate in D_2O . In all spectra, * indicates the solvent peaks.

Figure 3: Schematic of the amphiphilic nanoparticle synthesis. (A) This panel shows the preparation of the one-phase chemical reduction reaction using ethanol as solvent. (B) Gold-thiolate complex is allowed to form before the addition of a reducing agent. At this stage, the solution of gold salt became turbid. (C) During the dropwise addition of the reducing agent, gold nanoparticles are formed.

Figure 4: Cleanliness of the nanoparticles from unreacted free ligands. (A) This panel shows the ^1H NMR spectrum of the nanoparticles right after the synthesis and vacuum-drying. D_2O is used as the solvent for the ^1H NMR analysis. Sharp peaks shown by red arrows indicate the existence of free unbound ligands. (B) This panel shows the ^1H NMR spectrum of the nanoparticles after a

thorough purification (*i.e.*, washes and centrifugation with ethanol and DI water). The red arrow points to the magnified part of the spectrum, in which the peaks are broad, not sharp as before indicating the absence of free ligands. In both spectra, * indicates the solvent peaks.

Figure 5: Size distribution of nanoparticles. (A) This panel shows a representative TEM image of MUS:OT nanoparticles. The scale bar is 20 nm. (B) This panel shows a histogram of the core size of nanoparticles based on several TEM images. (C) UV-Vis spectra of the nanoparticles showed the characteristic surface plasmon resonance peak of the nanoparticles at around 520 nm.

Figure 6: Ligand ratio calculation. (A) This panel shows representative NMR spectra of combinations of disulfides (as references for ligands after core etching) and peak assignments for different protons in MeOD-d₄. (B) This panel shows ¹H NMR spectra of etched nanoparticles in MeOD-d₄. In all spectra, * indicates the solvent peaks.

Figure 7: Ligand density analysis. A TGA measurement of the nanoparticles was done to determine the ratio and density of organic material (ligands). The graph of the measurements is plotted as the weight percentage vs. the temperature. OT desorbs first, between 176 °C to 233 °C (vertical lines). MUS degrades to smaller molecules and is totally burned at around 800 °C. The remaining weight percentage corresponds to the gold core of the nanoparticles.

Figure 8: Comparison of stoichiometric and NMR ratios of OT on the particles. It is possible to tune the amphiphilicity of the nanoparticles by changing the starting stoichiometric ratio between MUS and OT in the reaction. The error bars show the upper and lower limit of OT content acquired using the indicated stoichiometric ratios. Stoichiometric ratios of 10%, 20%, *etc.*, up to 90% OT, were synthesized to observe the limits of OT content on the nanoparticle surfaces.

DISCUSSION:

This protocol describes first the synthesis of MUS ligand and, then, the synthesis and characterization of amphiphilic MUS:OT gold nanoparticles. Synthesizing MUS with minimal salt content enables a better reliability of the stoichiometric ratio between the ligands during the nanoparticle synthesis, which is a key factor for the reproducible synthesis of MUS:OT nanoparticles with a target hydrophobic content (**Figure 8**). The use of methanol as a common solvent for MUS and OT, along with the synthesis of the particles in ethanol, allows for a reliable synthesis of MUS:OT gold nanoparticles. The methods of characterization presented here make up a minimal list of experiments necessary to acquire sufficient information on the nanoparticles to verify the outcome of their synthesis.

There are four critical steps in this protocol: (i) the synthesis of MUS with a low salt content along with the removal of colored impurities in the second step and a crystallization of pure MUS in the end; (ii) tuning and determining the stoichiometric ratio between MUS and OT; (iii) the workup of the nanoparticles; and (iv) the characterization of the nanoparticles.

During the formation of nanoparticles, MUS preferentially binds to the nanoparticle surfaces,

which might be related to the solubility of the resulting nanoparticles. For example, a 2:1 stoichiometric feed ratio between MUS and OT results in 15% of OT on the surface when calculated using the data from the ^1H NMR of etched gold nanoparticles. Therefore, a higher content of OT must be used during the synthesis of the particles (**Figure 8**) to obtain a nanoparticle with a lower MUS to OT ratio; in other words, a more hydrophobic particle. In order to assess the stoichiometric ratio between the ligands on the surface of the nanoparticles, it is necessary to ensure there are no unbound ligands in the solution. The presence of unbound ligands affects the determination of the ligand ratio on the nanoparticles and the density, along with subsequent tests and experiments that may lead to incorrect interpretations. Repetitive cleaning cycles with different solvents (such as ethanol and DI water) are required to eliminate all unbound ligands and other impurities (byproducts of sodium borohydride, gold ions, *etc.*). ^1H NMR is important to confirm the purity of the nanoparticles. The line-broadening effect of ligands owing to the complex chemical environment on the nanoparticles broaden the peaks corresponding to the ligands, while any sharp signal comes from unbound molecules²². Furthermore, due to restricted mobility, the NMR peaks corresponding to the methylene adjacent to the thiol groups cannot be detected, which is another signature of the nanoparticle when inspected using ^1H NMR. Once the nanoparticles are clean, then the metal core is etched with iodine. Iodine etching is a well-established method to quantify the ligand ratio on nanoparticles. For instance, two decades ago, Murray *et al.* reported the determination of monolayer composition on gold nanoparticles after iodine etching, in which the iodine decomposes the gold core and releases the thiolate ligands as disulfides²³. The reliability of the iodine etching method has been established using other methods; for example, Harkness *et al.* reported that the ligand ratio obtained from NMR is within 1% deviation from mass spectroscopy measurements²⁴.

TGA is a straightforward method to calculate the organic content on the nanoparticles. The estimation of the surface ligand density assumes that all thiolate ligands bind to surface gold atoms and all free ligands have been removed during purification. To determine the ligand density, several assumptions are made, mainly that the particles are spherical, which is used to calculate the surface area, as well as the packing density, of the gold core. TEM provides a size distribution of the nanoparticle gold cores that can be used to calculate the approximate surface area of a nanoparticle. The nanoparticle synthesis described here produces a polydisperse population of particles with an average diameter of 2 - 3 nm and a size deviation of up to 30%. Also, the average radius, used to calculate the average volume of one particle (approximating the particles to spheres), combined with the density of gold, enables the calculation of the mass of one nanoparticle. Then, the mass measured by TGA over 800 °C enables the calculation of the number of particles initially present. By using this value and the average core size, the total surface area of the gold nanoparticles can be estimated. The ligand ratio calculated from the data acquired with ^1H NMR spectroscopy allows for the calculation of the number of moles of the ligands on the surface of the nanoparticles. The molar ratio between the ligands over the surface area of gold nanoparticles provides the ligand density (**Figure 7**). Clean nanoparticles have approximately 4 ligands per nm^2 . TGA data can also be used to estimate the ligand ratio, if the temperature interval in which they desorb from the gold surface is known for each ligand, and desorption occurs at separate temperature ranges.

In summary, this protocol provides a straightforward way to synthesize the MUS ligand with a low salt content and MUS:OT amphiphilic gold nanoparticles. One of the key factors of the reproducibility of these nanoparticles is the low inorganic salt content in the MUS used. These nanoparticles are stable both as powder and in solution (*e.g.*, H₂O and physiologically-relevant ones), which should be emphasized as a prerequisite for many applications. Thorough characterization of the size and the surface properties of amphiphilic nanoparticles is essential for future applications in which the degree of amphiphilicity may play a key role.

ACKNOWLEDGMENTS:

Z.P.G. and F.S. thank the Swiss National Science Foundation and, specifically, NCCR 'Molecular Systems Engineering'. Z.L. and F.S. thank the support of the Swiss National Science Foundation Division II grant. All authors thank Quy Ong for fruitful discussions and for proofreading the manuscript.

DISCLOSURES:

The authors have nothing to disclose.

REFERENCES:

1. Verma, A. *et al.* Effect of surface properties on nanoparticle-cell interactions. *Small*. **6** (1), 12-21 (2010).
2. Yeh, Y.-C. *et al.* Gold nanoparticles: preparation, properties, and applications in bionanotechnology. *Nanoscale*. **4** (6), 1871-1880 (2012).
3. Mirza, A. Z. A novel drug delivery system of gold nanorods with doxorubicin and study of drug release by single molecule spectroscopy. *Journal of Drug Targeting*. **23** (1), 52-58 (2015).
4. Mirza, A. Z., *et al.* Fabrication and characterization of doxorubicin functionalized PSS coated gold nanorod. *Arabian Journal of Chemistry*. In Press (2014).
5. Nel, A. E. *et al.* Understanding biophysicochemical interactions at the nano-bio interface. *Nature Materials*. **8** (7), 543-557 (2009).
6. Yeo, E. L. L. *et al.* Protein Corona around Gold Nanorods as a Drug Carrier for Multimodal Cancer Therapy. *ACS Biomaterials Science and Engineering*. **3** (6), 1039-1050 (2017).
7. Lin, J. *et al.* Cell membranes open "doors" for cationic nanoparticles/ biomolecules: Insights into uptake kinetics. *ACS Nano*. **7** (12), 10799-10808 (2013).
8. Saha, K. *et al.* Regulation of Macrophage Recognition through the Interplay of Nanoparticle Surface Functionality and Protein Corona. *ACS Nano*. **10** (4), 4421-4430 (2016).
9. Moyano, D. F. *et al.* Fabrication of corona-free nanoparticles with tunable hydrophobicity. *ACS*

Nano. **8** (7), 6748-6755 (2014).

10. Pengo, P. *et al.* Gold nanoparticles with patterned surface monolayers for nanomedicine: current perspectives. *European Biophysics Journal.* **46** (8), 749-771 (2017).

11. Kuna, J. J. *et al.* The effect of nanometre-scale structure on interfacial energy. *Nature Materials.* **8** (10), 837-842 (2009).

12. Verma, A. *et al.* Surface-structure-regulated cell-membrane penetration by monolayer-protected nanoparticles. *Nature Materials.* **7** (7), 588-595 (2008).

13. Van Lehn, R. C. *et al.* Lipid tail protrusions mediate the insertion of nanoparticles into model cell membranes. *Nature Communications.* **5**, 4482-4493 (2014).

14. Cagno, V. *et al.* Broad-spectrum non-toxic antiviral nanoparticles with a virucidal inhibition mechanism. *Nature Materials.* **17** (2), 195-203 (2018).

15. Uzun, O. *et al.* Water-soluble amphiphilic gold nanoparticles with structured ligand shells. *Chemical Communications.* (2), 196-198 (2008).

16. Huang, R. *et al.* Colloidal stability of self-assembled monolayer-coated gold nanoparticles: The effects of surface compositional and structural heterogeneity. *Langmuir.* **29** (37), 11560-11566 (2013).

17. Carney, R. P. *et al.* Electrical method to quantify nanoparticle interaction with lipid bilayers. *ACS Nano.* **7** (2), 932-942 (2013).

18. Van Lehn, R. C. *et al.* Effect of particle diameter and surface composition on the spontaneous fusion of monolayer-protected gold nanoparticles with lipid bilayers. *Nano Letters.* **13** (9), 4060-4067 (2013).

19. Huang, R. *et al.* Effects of surface compositional and structural heterogeneity on nanoparticle-protein interactions: Different protein configurations. *ACS Nano.* **8** (6), 5402-5412 (2014).

20. Van Lehn, R. C. *et al.* Free energy change for insertion of charged, monolayer-protected nanoparticles into lipid bilayers. *Soft Matter.* **10** (4), 648-658 (2014).

21. Ong, Q. *et al.* Characterization of Ligand Shell for Mixed-Ligand Coated Gold Nanoparticles. *Accounts of Chemical Research.* **50** (8), 1911-1919 (2017).

22. Marbella, L. E. *et al.* NMR techniques for noble metal nanoparticles. *Chemistry of Materials.* **27** (8), 2721-2739 (2015).

23. Templeton, A. C. *et al.* Reactivity of Monolayer-Protected Gold Cluster Molecules : Steric

657 Effects. *Journal of American Chemical Society*. **120** (8), 1906-1911 (1998).

658

659 24. Harkness, K. M. *et al.* A structural mass spectrometry strategy for the relative quantitation of
660 ligands on mixed monolayer-protected gold nanoparticles. *Analytical Chemistry*. **82** (22), 9268-
661 9274 (2010).

662







Figure 2








Figure 4




[Click here to access/download:Figure 4](#)


Figure 5

[Click here to access/download;Figure;jove figure 5.ai](#) 

a



b



c




Figure 6

[Click here to access/download;Figure;joive figure 6.ai](#)





Figure 7

[Click here to access/download;Figure;jove figure 7.ai](#)





Figure 8

[Click here to access/download;Figure;jove figure 8.tif](#)



NMR ratio of OT (%)

Stoichiometric ratio of OT (%)



Name of Material/ Equipment	Company	Catalog Number	Comments/Description
11-bromo-1-undecene	Sigma Aldrich	467642-25 ml	
Sodium Sulfite	Sigma Aldrich	S0505-250 g	
Benzyltriethyl-ammonium bromide	Sigma Aldrich	147125-25 g	
Methanol	VWR	BDH1135-2.5 LP	
DI water	Millipore	ZRXQ003WW	Deionized water
1 L round bottom flask	DURAN	24 170 56	
Diethyl ether	Sigma Aldrich	1.00930 EMD Millipore	
Stirring bar	Sigma Aldrich	Z329207,	
Dow Corning High Vacuum Grease	Sigma Aldrich	Z273554 ALDRICH	
Filtering flask	DURAN	20 201 63	
Filtering Buchner Funnel	FisherSci	11707335	
Ethanol >99.8%, ACS, Reagent	VWR	2081.321DP	
Deuterium dioxide	Sigma Aldrich	151882 ALDRICH	
Thioacetic acid 96%	Sigma Aldrich	T30805 ALDRICH	
Carbon black	Sigma Aldrich	05105-1KG	
Celite	Sigma Aldrich	D3877 SIGMA-ALDRICH	Filtration medium
Condenser	Sigma Aldrich	Z531154	
Hydrochloric acid, ACS reagent 37%	Sigma Aldrich	320331 SIGMA-ALDRICH	
Sodium Hydroxide, BioXtra, pellets (anhydrous)	Sigma Aldrich	S8045 SIGMA-ALDRICH	
Centrifuge tubes	VWR	525-0155P	
250 mL round bottom flask	DURAN	24 170 37	
500 mL round bottom flask	DURAN	24 170 46	
Nitric acid, FACS reagent 70%	Sigma Aldrich	438073 SIGMA-ALDRICH	
Gold(III) chloride trihydrate >99.9% trace metal basis	Sigma Aldrich	520918 ALDRICH	
1-octanethiol >98.5%	Sigma Aldrich	471836 ALDRICH	
Sodium Borohydride purum p.a.>96%	Sigma Aldrich	71320 ALDRICH	
Separatory funnel	Sigma Aldrich	Z330655 SIGMA	
Funnel	DURAN	21 351 46	
2V folded filtering papers	Whatman	1202-150	

Amicon filters	Merck	UFC903024
Iodine, ACS reagent, >99.8%, solid	Sigma Aldrich	207772 SIGMA-ALDRICH
5 mm NMR-Tubes, Type 5HP (high precision)	Armar	32210.503 Length 178 mm
Methanol-d4 99.8 atom%D	Armar	16400.2035
TGA crucible	Thepro	9095-9270.45
400 mesh carbon supported copper grid	Electron Microscopy Science	CF400-Cu
quartz cuvette	Hellma Analytics	100-1-40



1 Alewife Center #200
Cambridge, MA 02140
tel. 617.945.9051
www.jove.com

ARTICLE AND VIDEO LICENSE AGREEMENT

Title of Article:

SYNTHESIS AND CHARACTERIZATION . . .

Author(s):

GUVEN, SILVA, CUP, CENDROUSKA, STELLACCI

Item 1 (check one box): The Author elects to have the Materials be made available (as described at

<http://www.jove.com/author>) via: ☒ Standard Access ☐ Open Access

Item 2 (check one box):

- ☒ The Author is NOT a United States government employee.
- ☐ The Author is a United States government employee and the Materials were prepared in the course of his or her duties as a United States government employee.
- ☐ The Author is a United States government employee but the Materials were NOT prepared in the course of his or her duties as a United States government employee.

ARTICLE AND VIDEO LICENSE AGREEMENT

1. **Defined Terms.** As used in this Article and Video License Agreement, the following terms shall have the following meanings: “**Agreement**” means this Article and Video License Agreement; “**Article**” means the article specified on the last page of this Agreement, including any associated materials such as texts, figures, tables, artwork, abstracts, or summaries contained therein; “**Author**” means the author who is a signatory to this Agreement; “**Collective Work**” means a work, such as a periodical issue, anthology or encyclopedia, in which the Materials in their entirety in unmodified form, along with a number of other contributions, constituting separate and independent works in themselves, are assembled into a collective whole; “**CRC License**” means the Creative Commons Attribution-Non Commercial-No Derivs 3.0 Unported Agreement, the terms and conditions of which can be found at: <http://creativecommons.org/licenses/by-nc-nd/3.0/legalcode>; “**Derivative Work**” means a work based upon the Materials or upon the Materials and other pre-existing works, such as a translation, musical arrangement, dramatization, fictionalization, motion picture version, sound recording, art reproduction, abridgment, condensation, or any other form in which the Materials may be recast, transformed, or adapted; “**Institution**” means the institution, listed on the last page of this Agreement, by which the Author was employed at the time of the creation of the Materials; “**JoVE**” means MyJoVE Corporation, a Massachusetts corporation and the publisher of *The Journal of Visualized Experiments*; “**Materials**” means the Article and / or the Video; “**Parties**” means the Author and JoVE; “**Video**” means any video(s) made by the Author, alone or in conjunction with any other parties, or by JoVE or its affiliates or agents, individually or in collaboration with the Author or any other parties, incorporating all or any portion of the Article, and in which the Author may or may not appear.

2. **Background.** The Author, who is the author of the Article, in order to ensure the dissemination and protection of the Article, desires to have the JoVE publish the Article and create and transmit videos based on the Article. In furtherance of such goals, the Parties desire to memorialize in this Agreement the respective rights of each Party in and to the Article and the Video.

3. **Grant of Rights in Article.** In consideration of JoVE agreeing to publish the Article, the Author hereby grants to JoVE, subject to **Sections 4** and **7** below, the exclusive, royalty-free, perpetual (for the full term of copyright in the Article, including any extensions thereto) license (a) to publish, reproduce, distribute, display and store the Article in all forms, formats and media whether now known or hereafter developed (including without limitation in print, digital and electronic form) throughout the world, (b) to translate the Article into other languages, create adaptations, summaries or extracts of the Article or other Derivative Works (including, without limitation, the Video) or Collective Works based on all or any portion of the Article and exercise all of the rights set forth in (a) above in such translations, adaptations, summaries, extracts, Derivative Works or Collective Works and (c) to license others to do any or all of the above. The foregoing rights may be exercised in all media and formats, whether now known or hereafter devised, and include the right to make such modifications as are technically necessary to exercise the rights in other media and formats. If the “Open Access” box has been checked in **Item 1** above, JoVE and the Author hereby grant to the public all such rights in the Article as provided in, but subject to all limitations and requirements set forth in, the CRC License.

ARTICLE AND VIDEO LICENSE AGREEMENT

4. Retention of Rights in Article. Notwithstanding the exclusive license granted to JoVE in **Section 3** above, the Author shall, with respect to the Article, retain the non-exclusive right to use all or part of the Article for the non-commercial purpose of giving lectures, presentations or teaching classes, and to post a copy of the Article on the Institution's website or the Author's personal website, in each case provided that a link to the Article on the JoVE website is provided and notice of JoVE's copyright in the Article is included. All non-copyright intellectual property rights in and to the Article, such as patent rights, shall remain with the Author.

5. Grant of Rights in Video – Standard Access. This **Section 5** applies if the "Standard Access" box has been checked in **Item 1** above or if no box has been checked in **Item 1** above. In consideration of JoVE agreeing to produce, display or otherwise assist with the Video, the Author hereby acknowledges and agrees that, Subject to **Section 7** below, JoVE is and shall be the sole and exclusive owner of all rights of any nature, including, without limitation, all copyrights, in and to the Video. To the extent that, by law, the Author is deemed, now or at any time in the future, to have any rights of any nature in or to the Video, the Author hereby disclaims all such rights and transfers all such rights to JoVE.

6. Grant of Rights in Video – Open Access. This **Section 6** applies only if the "Open Access" box has been checked in **Item 1** above. In consideration of JoVE agreeing to produce, display or otherwise assist with the Video, the Author hereby grants to JoVE, subject to **Section 7** below, the exclusive, royalty-free, perpetual (for the full term of copyright in the Article, including any extensions thereto) license (a) to publish, reproduce, distribute, display and store the Video in all forms, formats and media whether now known or hereafter developed (including without limitation in print, digital and electronic form) throughout the world, (b) to translate the Video into other languages, create adaptations, summaries or extracts of the Video or other Derivative Works or Collective Works based on all or any portion of the Video and exercise all of the rights set forth in (a) above in such translations, adaptations, summaries, extracts, Derivative Works or Collective Works and (c) to license others to do any or all of the above. The foregoing rights may be exercised in all media and formats, whether now known or hereafter devised, and include the right to make such modifications as are technically necessary to exercise the rights in other media and formats. For any Video to which this Section 6 is applicable, JoVE and the Author hereby grant to the public all such rights in the Video as provided in, but subject to all limitations and requirements set forth in, the CRC License.

7. Government Employees. If the Author is a United States government employee and the Article was prepared in the course of his or her duties as a United States government employee, as indicated in **Item 2** above, and any of the licenses or grants granted by the Author hereunder exceed the scope of the 17 U.S.C. 403, then the rights granted hereunder shall be limited to the maximum rights permitted under such

statute. In such case, all provisions contained herein that are not in conflict with such statute shall remain in full force and effect, and all provisions contained herein that do so conflict shall be deemed to be amended so as to provide to JoVE the maximum rights permissible within such statute.

8. Likeness, Privacy, Personality. The Author hereby grants JoVE the right to use the Author's name, voice, likeness, picture, photograph, image, biography and performance in any way, commercial or otherwise, in connection with the Materials and the sale, promotion and distribution thereof. The Author hereby waives any and all rights he or she may have, relating to his or her appearance in the Video or otherwise relating to the Materials, under all applicable privacy, likeness, personality or similar laws.

9. Author Warranties. The Author represents and warrants that the Article is original, that it has not been published, that the copyright interest is owned by the Author (or, if more than one author is listed at the beginning of this Agreement, by such authors collectively) and has not been assigned, licensed, or otherwise transferred to any other party. The Author represents and warrants that the author(s) listed at the top of this Agreement are the only authors of the Materials. If more than one author is listed at the top of this Agreement and if any such author has not entered into a separate Article and Video License Agreement with JoVE relating to the Materials, the Author represents and warrants that the Author has been authorized by each of the other such authors to execute this Agreement on his or her behalf and to bind him or her with respect to the terms of this Agreement as if each of them had been a party hereto as an Author. The Author warrants that the use, reproduction, distribution, public or private performance or display, and/or modification of all or any portion of the Materials does not and will not violate, infringe and/or misappropriate the patent, trademark, intellectual property or other rights of any third party. The Author represents and warrants that it has and will continue to comply with all government, institutional and other regulations, including, without limitation all institutional, laboratory, hospital, ethical, human and animal treatment, privacy, and all other rules, regulations, laws, procedures or guidelines, applicable to the Materials, and that all research involving human and animal subjects has been approved by the Author's relevant institutional review board.

10. JoVE Discretion. If the Author requests the assistance of JoVE in producing the Video in the Author's facility, the Author shall ensure that the presence of JoVE employees, agents or independent contractors is in accordance with the relevant regulations of the Author's institution. If more than one author is listed at the beginning of this Agreement, JoVE may, in its sole discretion, elect not take any action with respect to the Article until such time as it has received complete, executed Article and Video License Agreements from each such author. JoVE reserves the right, in its absolute and sole discretion and without giving any reason therefore, to accept or decline any work submitted to JoVE. JoVE and its employees, agents and independent contractors shall have

ARTICLE AND VIDEO LICENSE AGREEMENT

full, unfettered access to the facilities of the Author or of the Author's institution as necessary to make the Video, whether actually published or not. JoVE has sole discretion as to the method of making and publishing the Materials, including, without limitation, to all decisions regarding editing, lighting, filming, timing of publication, if any, length, quality, content and the like.

11. **Indemnification.** The Author agrees to indemnify JoVE and/or its successors and assigns from and against any and all claims, costs, and expenses, including attorney's fees, arising out of any breach of any warranty or other representations contained herein. The Author further agrees to indemnify and hold harmless JoVE from and against any and all claims, costs, and expenses, including attorney's fees, resulting from the breach by the Author of any representation or warranty contained herein or from allegations or instances of violation of intellectual property rights, damage to the Author's or the Author's institution's facilities, fraud, libel, defamation, research, equipment, experiments, property damage, personal injury, violations of institutional, laboratory, hospital, ethical, human and animal treatment, privacy or other rules, regulations, laws, procedures or guidelines, liabilities and other losses or damages related in any way to the submission of work to JoVE, making of videos by JoVE, or publication in JoVE or elsewhere by JoVE. The Author shall be responsible for, and shall hold JoVE harmless from, damages caused by lack of sterilization, lack of cleanliness or by contamination due to the making of a video by JoVE its employees, agents or independent contractors. All sterilization, cleanliness or decontamination procedures shall be solely the responsibility of the Author and shall be undertaken at the Author's

expense. All indemnifications provided herein shall include JoVE's attorney's fees and costs related to said losses or damages. Such indemnification and holding harmless shall include such losses or damages incurred by, or in connection with, acts or omissions of JoVE, its employees, agents or independent contractors.

12. **Fees.** To cover the cost incurred for publication, JoVE must receive payment before production and publication the Materials. Payment is due in 21 days of invoice. Should the Materials not be published due to an editorial or production decision, these funds will be returned to the Author. Withdrawal by the Author of any submitted Materials after final peer review approval will result in a US\$1,200 fee to cover pre-production expenses incurred by JoVE. If payment is not received by the completion of filming, production and publication of the Materials will be suspended until payment is received.

13. **Transfer, Governing Law.** This Agreement may be assigned by JoVE and shall inure to the benefits of any of JoVE's successors and assignees. This Agreement shall be governed and construed by the internal laws of the Commonwealth of Massachusetts without giving effect to any conflict of law provision thereunder. This Agreement may be executed in counterparts, each of which shall be deemed an original, but all of which together shall be deemed to be one and the same agreement. A signed copy of this Agreement delivered by facsimile, e-mail or other means of electronic transmission shall be deemed to have the same legal effect as delivery of an original signed copy of this Agreement.

A signed copy of this document must be sent with all new submissions. Only one Agreement required per submission.

CORRESPONDING AUTHOR:

Name: FRANCESCO STELLACCI
Department: INSTITUTE OF MATERIALS
Institution: EPFL
Article Title: SYNTHESIS AND CHARACTERIZATION
Signature: [Signature] Date: 7/9/2018

Please submit a signed and dated copy of this license by one of the following three methods:

- 1) Upload a scanned copy of the document as a pdf on the JoVE submission site;
- 2) Fax the document to +1.866.381.2236;
- 3) Mail the document to JoVE / Attn: JoVE Editorial / 1 Alewife Center #200 / Cambridge, MA 02139

For questions, please email submissions@jove.com or call +1.617.945.9051

Reviewer 1

The authors present a preparation of gold nanoparticles with a mixed ligand shell of a hydrophobic and hydrophilic ligand at a carefully selected ratio intended to give stability under biological conditions and to also be useful for delivering drugs to cell membranes. This is an important topic of broad utility. A good detailed synthesis of the 11-mercaptoundecane sulfonic acid ligand is provided in addition to synthesis and modification procedure for the nanoparticles. It seems enough information is provided for others to try the procedure.

Please provide more references or a little bit more discussion on how the iodine etching method for determining the ligand ratio works and how reliable it is. Why does it say a ratio of 66:34 is desired but on line 90 a 50:50 ratio is mentioned? Please run spell check, for example on line 113 we have 'undec-10-enefulfonate'.

We thank Reviewer 1 for the comments. A more detailed discussion about iodine etching is added to the discussion part of the paper. Line 449 - 455.

The ratios of nanoparticles were corrected. Line 100.

Spell check was run on the manuscript.

Reviewer 2

Guven et al. demonstrated a protocol to synthesize of amphiphilic gold nanoparticles by using MUS and OT as ligand shell. Then the prepared nanoparticles are characterized by NMR, TGA, TEM, UV-Vis techniques to identify the ligand ratios of MIS and OT. As authors mentioned, the use of MUS ligand with low inorganic salt content is a key point to prepare the reproducibility of the gold nanoparticles. Thus, the protocol of the synthesis of MUS ligand with low content of inorganic salt is the major part in this manuscript. The reproducibility, high salt and pH tests for the prepared AuNPs are lacked in the manuscript. Overall, this manuscript provided a reasonable procedure of the synthesis of MUS and eventually can be published after major corrections.

Could the provided protocol (MUS/OT as ligand shell and NaBH₄ as reducing agent) be also used for the preparation of amphiphilic silver nanoparticles?




How about using 11-Mercaptoundecanoic acid to replace 11-mercapto-1-undcanesulfonate? It can reduce the synthesized procedure of 11-mercapto-1-undcanesulfonate.

Figure 5 is missed in the manuscript. According to manuscript, the diameter of the prepared AuNPs are about 2-3 nm. As we known, the smaller size of AuNPs, the less





stability of long-term storage. How about the stability of the prepared AuNPs? Is it possible to prepare larger size of AuNPs ($\sim 13\text{-}15\text{ nm}$)? How to do it?

We thank Reviewer 2 for the comments. The reproducibility of the nanoparticle synthesis protocol was provided in the Figure 8. 3 different batches of MUS:OT 2:1 nanoparticles were synthesized and resulted in nanoparticles with an average of 12% OT on the surface. The reaction is supposed to be performed under the conditions specified avoiding changes in salt and pH, this is implicitly discussed when we say that the starting materials (MUS) should be free of extra salt.

1-Silver nanoparticles were synthesized following the same protocol. Particles with a core diameter of $2.8 \pm 1.3\text{ nm}$ were obtained using this synthesis. The ^1H -NMR characterization revealed the amount of OT on the surface was 20%, slightly higher than equivalent gold nanoparticles. However, contrary to the gold nanoparticles, silver nanoparticles were less water soluble. All the characterization results are depicted in Figure 1.



2- To produce amphiphilic nanoparticles phosphonic acid (11-mercaptophosphonic acid, MUP) terminated ligands were used instead of MUS. The synthesis resulted in 3.13 ± 1.4 nm core size with 7% OT on the surface (calculated using $^1\text{H-NMR}$ of the etched particles). TGA and calculations revealed 5 ligands per nm^2 , similar to 2:1 MUS:OT nanoparticles. However, the solubility of MUP:OT, amphiphilic nanoparticles in physiological buffers is drastically lower than that of MUS:OT nanoparticles. MUP:OT nanoparticles dissolve in basic solutions, as well as water-ethanol mixtures. Therefore, in our experience amphiphilic nanoparticles having sulfonated ligands on the surface are more colloiddally robust in physiological buffers compared to other amphiphilic nanoparticles tested. All the characterization results are depicted in Figure 2.



3- Figure 5 is added. The stability of the prepared AuNP is extremely high. No distinct degradation of MUS:OT gold nanoparticles could be seen after 1 year. This synthesis method does not result in nanoparticles larger than the dimensions reported in this protocol.

The chemical names were corrected and a spellcheck was ran throughout the manuscript.

Reviewer 3

The manuscript "Synthesis and Characterization of Amphiphilic Gold Nanoparticles therapy by Guvenet al., underwent review and work was found scientifically sound and well structured. The discussion of the manuscript is also very well written.

This work is dedicated to the one-phase chemical reduction followed by thorough purification to generate these nanoparticles. This approach seems promising. However, the submitted manuscript provokes some questions and comments (see below).

1 The level of English is not good especially in introduction.

2 Generally in abstract references should be avoided.

3 Line 44 what is the meaning of this sentence "in water 9combined with"

4 Line 71, remove 9 from start of next sentence "9 Moreover, these"

5 The author does not refer the current published articles dedicated to the synthesis of traditional methods. Please incorporate these references in revised manuscript, a Mirza, A.Z., Shamshad, H. Fabrication and characterization of doxorubicin functionalized PSS coated gold nanorod. Arabian Journal of Chemistry (2014), <http://dx.doi.org/10.1016/j.arabjc.2014.08.009>.

c Eugenia Li Ling Yeo, Joshua U-Jin Cheah, Bing Yi Lim, Patricia Soo Ping Thong, Khee Chee Soo, and James Chen Yong Kah, Protein Corona around Gold Nanorods as a Drug Carrier for Multimodal Cancer Therapy, ACS Biomater. Sci. Eng., 2017, 3 (6), pp 1039-1050.

b Mirza, A.Z., A novel drug delivery system of gold nanorods with doxorubicin and study of drug release by single molecule spectroscopy, Journal of Drug Targeting, Volume 23, Issue 1, 2015, Pages 52-58.

6 Author should mention name of chemical with abbreviation then use abbreviation throughout the manuscript for example "11-mercaptoundecane sulfonic acid (MUS)".

7 Line 166 something missing after chemical name "1.3. 11-mercapto-1-undecanesulfonate (MUS):"?

8 Why author mention protocol in numbering not in paragraph?.

9 ml and µl should be mL and µL throughout the manuscript.

10 There is missing of Figure 5. Size distribution of nanoparticles in manuscript. Please provide image of TEM.

This paper should be accepted after major revision.

1- We have improved the level of the technical English employed throughout the text.

2- References in the abstract were removed.

3- It was a misspelling and it was corrected. Line 79

4- Misspelling was corrected.

5- The references were added. Lines 66 and 67.

6- Abbreviations were mentioned once and used throughout the manuscript.

- 7- There was not missing part on the sentence. '11-mercaptoundecane-1-undecanesulfonate (MUS)' in line 215 represents the headline of the 3rd and final step of overall MUS ligand synthesis.
- 8- The format of the JOVE paper requests the protocol with numbering.
- 9- The units were corrected throughout the manuscript.
- 10- Figure 5 is provided.