

# Journal of Visualized Experiments

## A Continuous-Flow Photocatalytic Reactor for Precisely-Controlled Deposition of Metallic Nanoparticles

--Manuscript Draft--

|  |  |
|--|--|
| <b>Article Type:</b>   | Invited Methods Article - JoVE Produced Video  |
| <b>Manuscript Number:</b>  | JoVE58883R2  |
| <b>Full Title:</b>   | A Continuous-Flow Photocatalytic Reactor for Precisely-Controlled Deposition of Metallic Nanoparticles   |
| <b>Keywords:</b>   | Platinum nanoparticles; gold nanoparticles; TiO2 nanocomposite; Metallic nanoparticles; Partially reduced graphene oxide; Photocatalytic deposition; Continuous flow reactor; Photoreduction |
| <b>Corresponding Author:</b>   | Selmiye Gürsel, PhD<br>Sabanci Universitesi<br>Istanbul, TURKEY  |
| <b>Corresponding Author's Institution:</b>   | Sabanci Universitesi   |
| <b>Corresponding Author E-Mail:</b>  | selmiye@sabanciuniv.edu  |
| <b>Order of Authors:</b>   | Sina Abdolhosseinzadeh<br>Mirsajjad Mousavi<br>Navid Haghmoradi<br>Selmiye Gürsel  |
| <b>Additional Information:</b>   |  |
| <b>Question</b>  | <b>Response</b>  |
| Please indicate whether this article will be Standard Access or Open Access.   | Standard Access (US\$2,400)  |
| Please indicate the <b>city, state/province, and country</b> where this article will be <b>filmed</b> . Please do not use abbreviations. | Tuzla, Istanbul, Turkey  |

**TITLE:****A Continuous-flow Photocatalytic Reactor for the Precisely Controlled Deposition of Metallic Nanoparticles****AUTHORS AND AFFILIATIONS:**

Sina Abdolhosseinzadeh<sup>1,2</sup>, Mirsajjad Mousavi<sup>3</sup>, Navid Haghmoradi<sup>3</sup>, Selmiye Alkan Gürsel<sup>3,4</sup>

<sup>1</sup>Institut des matériaux, École Polytechnique Fédérale de Lausanne (EPFL), Lausanne, Switzerland

<sup>2</sup>Laboratory for Functional Polymers, Swiss Federal Laboratories for Materials Science and Technology (Empa), Dübendorf, Switzerland

<sup>3</sup>Faculty of Engineering and Natural Sciences, Sabanci University, Istanbul, Turkey

<sup>4</sup>SUNUM Nanotechnology Research Centre, Sabanci University, Istanbul, Turkey

**Corresponding Author:**

Selmiye Alkan Gürsel (selmiye@sabanciuniv.edu)

T: +90-216-483-9573

**Email Addresses of Co-Authors:**

Sina Abdolhosseinzadeh (sina.abdolhosseinzadeh@epfl.ch)

Mirsajjad Mousavi (mousavi@sabanciuniv.edu)

Navid Haghmoradi (nhaghmoradi@sabanciuniv.edu)

**KEYWORDS:**

platinum nanoparticles, gold nanoparticles, TiO<sub>2</sub> nanocomposite, metallic nanoparticles, partially reduced graphene oxide, photocatalytic deposition, continuous flow reactor, photoreduction

**SUMMARY:**

For a continuous and scalable synthesis of noble-metal-based nanocomposites, a novel photocatalytic reactor is developed and its structure, operation principles, and product quality optimization strategies are described.

**ABSTRACT:**

In this work, a novel photocatalytic reactor for the pulsed and controlled excitation of the photocatalyst and the precise deposition of metallic nanoparticles is developed. Guidelines for the replication of the reactor and its operation are provided in detail. Three different composite systems (Pt/graphene, Pt/TiO<sub>2</sub>, and Au/TiO<sub>2</sub>) with monodisperse and uniformly distributed particles are produced by this reactor, and the photodeposition mechanism, as well as the synthesis optimization strategy, are discussed. The synthesis methods and their technical aspects are described comprehensively. The role of the ultraviolet (UV) dose (in each excitation pulse) on the photodeposition process is investigated and the optimum values for each composite system are provided.

**INTRODUCTION:**

Metallic nanoparticles, especially noble metals (e.g., Pt, Au, Pd) have vast applications in catalysis<sup>1</sup>. In general, decreasing the size of the nanoparticles (NPs) increases their catalytic

activity while maintaining the cost (weight) constant, but it also makes their application more difficult. NPs (usually smaller than 10 nm) have great tendencies to aggregation, which degrades their catalytic activity; however, immobilization on suitable substrates can mostly resolve this problem. Furthermore, depending on the application type (e.g., electrocatalysis), it is sometimes necessary to immobilize the NPs on conductive substrates<sup>2,3</sup>. NPs can also be hybridized with semiconductors to form a Schottky barrier and avoid (delay) the electron-hole recombination (acting as electron traps)<sup>4,5</sup>. Hence, in most of the applications, the noble metal NPs (NNPs) are deposited either on a conductive (e.g., graphene) or a semiconductive (e.g., TiO<sub>2</sub>) substrate. In both cases, metal cations are usually reduced in the presence of the substrate, and the reduction technique differs from one method to another.

For the deposition of NNPs via a reduction of their cations, electrons (with proper electrical potential) should be provided. That can be done in two ways: by oxidation of other chemical species (a reducing agent)<sup>6,7</sup> or from an external power source<sup>8</sup>. In any case, for the homogeneous deposition of monodispersed NPs, it is necessary to impose a strict control on the generation and transfer of the (reducing) electrons. This is very difficult when a reducing agent is used since there is virtually no control over the reduction process once the reactants (cations and reducing agent) are mixed. Furthermore, NPs can form anywhere and not necessarily on the target substrate. When using an external power source, the control over the number of the provided electrons is much better, but NPs can only be deposited on an electrode surface.

Photocatalytic deposition (PD) is an alternative approach, which offers more control over the number of the (photo)generated electrons since it is directly related to the dose of the illuminated photons (with a proper wavelength). In this method, the substrate material has a dual role; it provides the reducing electrons<sup>9</sup> and stabilizes the formed NPs<sup>10</sup>. Moreover, NPs form only on the substrate since the electrons are generated by the substrate. A proper electrical connection between composite components (made by the photocatalytic reduction method) is also guaranteed<sup>11</sup>. Nevertheless, in conventional photocatalytic deposition methods in which the whole batch of reactants (photocatalyst and metal cation) is illuminated simultaneously, there is no control over the nucleation of the NNPs. Indeed, once a few particles (nuclei) are formed, they act as preferred transfer sites for the photogenerated electrons<sup>5</sup> and act as a preferred growth site. This superior electron transfer promotes the growth of the existing particles and disfavors the formation of new nuclei, which results in the formation of large NNPs. This problem can be addressed by the pulsed illumination of UV light in a special continuous-flow reactor (**Figure 1**) that has recently been developed by our group<sup>12</sup>. The unique feature of this reactor is that it allows researchers to control both NP-size-determining factors, namely, nucleation and growth. In this reactor, a very small portion of reactants is illuminated for a very short period of time, promoting the formation of nuclei (more nuclei are formed) and restricting the growth (smaller particles are attained). In this method, by controlling the illumination dose (i.e., by adjusting the exposure duration [changing the length of uncovered parts of the reaction tube; **Figure 1C**] or intensity of the incident light [number of the lamps]), a very precise control over the number of photogenerated electrons and, consequently, on the reduction process (NNP deposition) can be exerted.

[Place **Figure 1** here]

Despite the great potential of the PD method for the controlled deposition of NNPs, its application is limited to semiconducting materials. Fortunately, it is possible to open a wide band gap in graphene (one of the best-conducting substrates<sup>13</sup>) by its simple chemical functionalization. Afterward, these functional groups (FGs) can be mostly removed and the resulting graphene will still be conductive enough for most of the applications. Among numerous functionalized derivatives of graphene, graphene oxide (GO), which exhibits considerable semiconducting properties<sup>14</sup>, is the most promising candidate for this purpose. This is mainly due to the fact that GO's production has the highest production yield among the others. Nevertheless, since GO consists of different types of FGs, its chemical composition varies continuously under UV illumination. We have recently shown that by a selective removal of weakly bonded FGs (partial reduction; PRGO), the chemical structure and electronic properties of GO can be stabilized, which is an essential requirement for homogeneous depositions of the NNPs<sup>12</sup>. In this report, we describe the structure of the reactor and provide detailed information for its replication and operation. The deposition mechanism (working mechanism of the reactor) and possible optimization strategies are also discussed in great detail. To validate the applicability of the developed PD reactor for both types of common substrates (conductor and semiconductor) and different NNPs, the deposition of platinum on PRGO and TiO<sub>2</sub>, as well as of gold on TiO<sub>2</sub>, is demonstrated. It is noteworthy that by a proper selection of the metal, photocatalyst and precursor materials (e.g., salt, hole scavenger), and the dispersion media, several other metallic particles (such as Ag and Pd<sup>15</sup>) can also be deposited. In principle—since, in the photodeposition of NNPs, the cations of the metal are reduced by the photoexcited electrons—the energy level of the semiconductor's conduction band minimum (CBM) should match with (be more negative than) the reduction potential of the aimed cations. Due to the extensive technical production aspects, the synthesis of PRGO is also described in detail. For further information regarding the chemical structure and electronic properties of PRGO, please refer to previous work<sup>12</sup>.

The detailed structure of the reactor is schematically depicted in **Figure 2**. The reactor has two main components: a UV illumination and a reservoir compartment. The illumination section consists of a quartz tube, which is exactly fixed along the central axis of a cylindrical tube with a polished aluminum liner. The reservoir consists of a 1 L sealed-cap glass bottle with gas and liquid (reactants) inlets and outlets. Use a silicon septum with an open-top screw cap for inserting the tubes. To take samples during the reaction without letting oxygen enter the reactor, an outlet with a valve is also installed. It should be mentioned here that the samplings on specific time intervals are not a part of the nanocomposite production process, and sampling only needs to be done once to obtain the concentration-time curves for each set of synthesis parameters (the application of these curves will be discussed in the Discussion section). The reservoir is placed inside an ice-water bath while being vigorously mixed on a magnetic stirrer. A magnetic pump circulates the reactant from the reservoir to the reaction chamber (illumination section) and back to the reservoir. A magnetic one is used since high flow rates are necessary (the flow rate in this work = 16 L·min<sup>-1</sup>) and peristaltic pumps (or other similar pumps) can hardly provide those flows. When using a magnetic pump, care should be taken to completely fill the impeller casing (pump housing) with the reactant liquid and evacuate any trapped air (oxygen source). The trapped air

can also decrease the pump's real flow rate.

For a pulsed excitation of the photocatalyst material, specific lengths of the quartz tube are covered by a thick aluminum foil, leaving equal lengths between them uncovered (**Figure 2**). The duration of the pulsed excitation can be adjusted by changing the length of the uncovered parts (exposure length). The optimum exposure length is determined by various parameters, such as the quantum yield of the photocatalyst and the intended NP loading (concentration of the precursors; see Discussion).

## **PROTOCOL:**

### **1. Fabrication and operation of the photocatalytic deposition reactor**

CAUTION: When UV lamps are turned on, use UV-C protective glasses.

#### **1.1. Fabrication of the photocatalytic deposition reactor**

1.1.1. Cover the inner surface of a polyvinyl chloride (PVC) pipe (diameter x length = 15 cm x 55 cm; other materials can also be used) with a thick, polished, and adhesive-backed aluminum foil. Install five 55 W UV-C lamps (see **Table of Materials**) on the inner surface of the tube at equal distance.

1.1.2. Fix a quartz tube (diameter x length = 0.5 cm x 55 cm) along the central axis of the PVC tube (concentric configuration). For the pulsed excitation of the photocatalyst, cover the desired equal lengths of the quartz tube with the same adhesive-backed aluminum foil (in this work, for the Pt/graphene composites: 5 cm x 0.4 cm, 5 cm x 2 cm, and 1 cm x 50 cm, and for the Pt/TiO<sub>2</sub> and Au/TiO<sub>2</sub> composites: 5 cm x 1 cm). Note that 2.5 cm of the quartz tube on each side is used for connecting the plastic tubes.

1.1.3. Install a heavy-duty fan at one end of the PVC tube (to cool down the whole illumination chamber).

[Place **Figure 2** here]

#### **1.2. Feeding the reactants to the reactor**

1.2.1. Use a setup like the one shown in **Figure 2**. Place a separation funnel in a higher vertical position than the pump and the reservoir (the pump should also be in a higher vertical position than the bottom of the reservoir) and fill the reactants into the separation funnel.

1.2.2. Open the valve  $V_0$  to feed the reactant to the reactor and close the valve ( $V_0$ ) immediately when the funnel is depleted (otherwise, air will also enter the pump).

**NOTE:** The flow rate of the magnetic pumps is affected by the gravitational forces exerted on the

liquid, meaning that any alteration in the position of the reactor parts (vertical displacements) will change the flow rate (thus, do not displace the reactor parts once they are set up).

## 2. Synthesis of partially reduced GO

CAUTION: All the following experiments should be carried out inside a fume hood.

### 2.1. Synthesis of GO

2.1.1. Add 100 mL of 98% sulfuric acid and 2 g of graphite to a 500 mL Erlenmeyer flask. Cool down the flask to  $\sim 0^{\circ}\text{C}$  in an ice-water bath while mixing its contents on a magnetic stirrer.

NOTE: Use a big magnetic stir bar, since the suspension will become very viscous at the end of the reaction.

2.1.2. Gradually add 6 g of potassium permanganate (over a period of 30 min) as it is a very exothermic reaction. Remove the ice-water bath and continue stirring for 6 h.

2.1.3. Put the flask inside an ice-water bath and continue stirring for 15 min. Add 250 mL of distilled water dropwise, using a separation funnel. Remove the ice-water bath, gradually add 30 mL of hydrogen peroxide, and keep stirring for 30 min.

2.1.4. Centrifuge the suspension at  $3,500 \times g$  for 15 min and discard the supernatant. Wash the precipitates with distilled water. Repeat this process (wash-centrifuge) till pH reaches 5.

NOTE: Higher rotational speeds (if available) would be better but lower speeds should be compensated with longer centrifugation times. Also note that when the pH value rises to above 3–4, even long-time centrifugation (and also higher rotational speeds) cannot precipitate all the particles<sup>16</sup> and a considerable part of the suspension will be lost (roughly 1 g will remain at the end). The reaction can be paused here (store the reactants in an amber bottle, or wrap a normal bottle with aluminum foil).

2.1.5. Add the product of the previous step to 0.5 L of 1 M hydrochloric acid and stir it for 1 h. Wash the product as described in step 2.1.3 until the pH reaches 5. Add the product to 1 L of distilled water and sonicate it in a bath-sonicator for 3 h (add ice to the bath during the sonication to avoid a temperature rise).

2.1.6. Centrifuge the product for 3x 20 min at  $3,500 \times g$  and, each time, discard the precipitates. Store the obtained GO suspension in a capped glass bottle (use an amber bottle, or wrap a normal bottle with aluminum foil).

NOTE: If necessary, the centrifuge times can be broken down to shorter intervals (with cooling periods in between) to avoid temperature rises (higher than room temperature [RT]) of the suspension since, otherwise, the unwanted precipitates will not settle down.

2.1.7. Weigh three dry crystallizing dishes (of a volume of 100–200 mL) with an analytical grade balance (0.01 mg readability), each of them 3x. Shake the GO suspension well and, after 1 min, add exactly (with the highest possible accuracy) 100 mL of it to each of the crystallizing dishes. Leave the dishes in a 70–80 °C oven to dry completely.

2.1.8. By means of the final dry weight (weigh each dish 3x on the same analytical balance) and empty dish weight, determine the solid content of the GO suspension by averaging the values obtained from the three dishes. Adjust the concentration to 0.2 g/L by adding the required amount of distilled water.

NOTE: To check if the drying is complete or not, check the weight changes during two consecutive days. The weighing should be done immediately after taking the dishes out of the oven (before the temperature falls below 50 °C) since, otherwise, considerable weight increase will be observed. Although this process is time-consuming, since the solid content is not high, it is more accurate than other solid-content-determination methods.

## **2.2. Partial reduction of GO (synthesis of PRGO)**

2.2.1. Gradually add the diluted GO suspension (the product of step 2.1.5) to an equal volume of a 4 M sodium hydroxide solution in a round-bottom flask. Attach a condenser to the flask and reflux-stir the suspension at 90 °C for 8 h (with a heater mantle).

2.2.2. After cooling down, “wash-centrifuge” the precipitates with distilled water (as described in step 2.1.4) to near neutral pH (~7–8).

NOTE: Since PRGO has much less hydrophilicity than GO, all the precipitates should settle down during the centrifugation and the supernatant should be a completely clear solution. If this is not the case for any reason (e.g., not sufficient rotational speed), the solid content measurement (see step 2.1.8) should be conducted at this stage too.

## **3. Photocatalytic deposition of NNPs**

### **3.1. Synthesis of Pt/graphene composite**

3.1.1. Adjust the concentration of the product from section 2.2 to 50 mg·L<sup>-1</sup> and sonicate the suspension with a probe sonicator for 1 h in an ice-water bath. Take 540 mL of the product and add 60 mL of ethanol (hole scavenger) and continue the sonication (in ice) for an extra 1 h. For a 20 wt% Pt/graphene composite, add 11.5 mg of 8 wt% hexachloroplatinic acid aqueous solution (commercially available) to the product and stir it at room temperature for 15 min (for other Pt loadings, calculate the amount accordingly).

NOTE: It is advised to use aqueous solutions of the noble metal salts (if commercially available) or initially prepare a highly concentrated stock solution from the powder-form salts. These salts

are hygroscopic materials and, due to their extensive water absorption, precise weighing and obtaining reproducible results will be difficult or even impossible.

3.1.2. Fill the ice-water bath with ice and feed the product of the previous step to the reactor, as described in section 1.2. Start the magnetic pump and open the N<sub>2</sub> gas inlet valve with a high flow. Put and fix the gas outlet tube (T<sub>1</sub> in **Figure 2**) in a 1 L Erlenmeyer flask and fill it with ~0.7 L of water so that the gas bubbles out.

3.1.3. To flush out the dissolved O<sub>2</sub> gas from the system and cool down the suspension, vigorously mix the suspension with the magnetic stirrer for 30 min. Reduce the N<sub>2</sub> gas flow and turn on the five UV lamps.

NOTE: The N<sub>2</sub> gas flow has no effect on the synthesis process itself and, hence, has no specific value. However, it is continuously applied to maintain a positive pressure inside the system and avoid O<sub>2</sub> penetration. Bubble formation at the endpoint of the T<sub>1</sub> tube inside the water-filled Erlenmeyer flask is the only requirement for the flow adjustment.

### 3.2. Sampling Pt/graphene deposition (and reduction of PRGO to RGO)

CAUTION: Although wearing goggles in a chemistry lab is always mandatory, it is worth it to be reminded again, since in this experiment, there is a high risk of splashing.

3.2.1. Increase the N<sub>2</sub> gas flow 5 min after turning on the UV lights. Attach a syringe to point P<sub>s</sub> (**Figure 2**). While holding the syringe piston to prevent it from coming out, open the valve V<sub>1</sub>, fill the syringe with 20 mL of the suspension, and close the valve (V<sub>1</sub>). Detach the syringe and open the valve V<sub>2</sub> to evacuate the remaining suspension inside the tube T<sub>2</sub>, and close it (V<sub>2</sub>) afterward. Reduce the N<sub>2</sub> gas flow to the previous level.

3.2.2. Centrifuge the product of the previous step at 10,000 x *g* for 10 min. Store the supernatant for inductively coupled plasma–optical emission spectrometry (ICP-OES) analysis. Wash the precipitates with distilled water and centrifuge it at 10,000 x *g* for 10 min (discard the supernatant this time). Repeat the washing process 1x more.

3.2.3. Disperse the product of the previous step in 50 mL of distilled water by gentle sonication in a bath sonicator for 1 h. Dissolve 1 mg of ascorbic acid and heat-stir it at 90 °C for 1 h. Centrifuge the product at 10,000 x *g* for 10 min, take the precipitates, and discard the supernatant.

3.2.4. Repeat the washing process 2x more and store the precipitates for characterization purposes.

3.2.5. Repeat steps 3.2.1 and 3.2.2 for sampling times of 10, 15, 20, 30, 45, 60, 75, 90, 105, and 120 min (after turning on the UV lights).



### **3.3. Synthesis of Pt/TiO<sub>2</sub> composite**

3.3.1. Add 200 mg of TiO<sub>2</sub> nanoparticles (commercially available, ~100–150 nm in particle size) to 570 mL of distilled water and 30 mL of ethanol and sonicate it with a probe sonicator in an ice-water bath for 1 h.

3.3.2. For a 5 wt.% Pt/TiO<sub>2</sub> composite, add 21 mg of 8 wt.% hexachloroplatinic acid aqueous solution to the prepared suspension and stir it at room temperature for 15 min (for other Pt loadings, calculate the amount accordingly). Repeat step 3.1.2 for the prepared mixture, with four and two UV lamps.

### **3.4. Sampling Pt/TiO<sub>2</sub> deposition**

3.4.1. Repeat section 3.2 for the products of section 3.3 at time intervals of 2.5, 5, 7.5, 10, 20, and 40 min.

### **3.5. Synthesis of Au/TiO<sub>2</sub> composite**

3.5.1. For a 5 wt.% Au/TiO<sub>2</sub> composite, add 345 µL of a 50 g·L<sup>-1</sup> hydrogen tetrachloroaurate(III) aqueous solution to the product of step 3.3.1 and stir it at room temperature for 15 min (for other Au loadings or other Au sources, calculate the amount accordingly). Repeat step 3.1.2 for the prepared mixture, with four and two UV lamps.

NOTE: Since the gold salt used here was in powder form, we initially prepared a 50 g·L<sup>-1</sup> hydrogen tetrachloroaurate(III) solution in distilled water.

### **3.6. Sampling Au/TiO<sub>2</sub> deposition**

3.6.1. Repeat section 3.2 for the products of section 3.5 at time intervals of 2.5, 5, 7.5, 10, 20, and 40 min.

## **4. Sample preparation for characterizations**

4.1. For ICP-OES analysis of supernatants, simply filter the liquids with polytetrafluoroethylene (PTFE) syringe filters with a 0.2 µm pore size. For more information on ICP-OES of the solid samples, refer to Ma and Wei<sup>17</sup>.

NOTE: When the samples are in solution form, ICP-OES is a very simple and fast technique, but for solid samples, especially for noble metals, it requires multiple microwave digestion processes with aqua regia, hydrogen peroxide, and hydrochloric acid, which makes it very time-consuming (at least 12 h for each sample preparation). Hence, for monitoring the photodeposition rate and process optimization, concentration changes of the metallic cations in the supernatant can be monitored.

4.2. For transmission electron microscopy (TEM) imaging, disperse collected precipitates in distilled water (a very dilute suspension) and drop-cast them on TEM grids (or dip-coat the grid into the suspension). For X-ray photoelectron spectroscopy (XPS) analysis, simply drop-cast concentrated dispersions of the precipitates on oxygen-plasma-treated glass substrates and dry them on a hot plate.

#### REPRESENTATIVE RESULTS:

XPS is one of the most powerful techniques for confirming the formation of metallic NPs and study their chemical states. For this purpose, both survey spectra and high-resolution spectra (of  $\text{Pt}_{4f}$  and  $\text{Au}_{4f}$ ) were recorded, which confirms the complete reduction of the metallic cations and successful deposition of the NNPs (**Figure 3**). For the deconvolution of both  $\text{Pt}_{4f}$  and  $\text{Au}_{4f}$ , initially, a Shirley background subtraction was performed. Afterward, the core-level spectra were decomposed into their components with mixed Gaussian/Lorentzian (70% Gaussian and 30% Lorentzian) lines by a nonlinear least-squares curve-fitting procedure, using the XPSPEAK 4.1 software. The reduced chi-square value for all the fittings was kept below 0.01. The binding energy separation of the  $\text{Pt}_{4f7/2}$  and  $\text{Pt}_{4f5/2}$  peaks was set to 3.33 eV and the intensity ratio between the  $\text{Pt}_{4f7/2}$  and  $\text{Pt}_{4f5/2}$  peaks was set to 0.75. Those values for  $\text{Au}_{4f7/2}$  and  $\text{Au}_{4f5/2}$  were 3.71 eV and 0.78, respectively.

[Place **Figure 3** here]

The distribution of the nanoparticles and their morphologies, which have significant effect on the performance of nanocomposite catalysts, have been studied by TEM. These two characteristics are affected by numerous synthesis parameters, but in this work, through the optimization of the illumination dose per exposure (IDE), we have been able to obtain a fairly monodisperse and uniformly distributed NNPs on both of the substrates (RGO and  $\text{TiO}_2$ ) (**Figure 4**).

[Place **Figure 4** here]

In the photocatalytic deposition of NNPs, since photoexcited electrons are responsible for the reduction of metallic cations, the reaction progress (NNP loading) can be studied by monitoring the concentration changes of the metallic cations. ICP-OES is one of the most accurate techniques for determining the cations concentration. The direct relation of the PD with IDE is clearly shown in these experiments, which provide significant insights and information for understanding the working mechanism of the developed reactor (**Figure 5**).

[Place **Figure 5** here]

Interestingly, by comparing the photodeposition rate (obtained from the ICP-OES results) for different synthesis conditions (**Table 1**), a direct relation between the number of photoexcited electrons and the amount of the deposited NNPs can be demonstrated (see Discussion). The working (deposition) mechanism of the developed reactor is also explained based on this data set.

[Place Table 1 here]

## FIGURE AND TABLE LEGENDS:

**Figure 1: The fabricated photocatalytic deposition reactor.** (A) The reactor. (B) Inside the illumination chamber. (C) A quartz tube with 5 cm x 1 cm illumination exposure length.

**Figure 2: Schematic illustration of the photocatalytic deposition reactor.** T<sub>1</sub> is the N<sub>2</sub> gas outlet that goes into the bubbler. T<sub>2</sub> is the sampling tube and Ps is the point for attachment of the syringe (for sampling). V<sub>0</sub> is the initial feeding valve and V<sub>1</sub> and V<sub>2</sub> are the sampling and tube evacuation valves (after sampling), respectively.

**Figure 3: XPS survey spectra.** Spectra for the (A) Pt/graphene composite, (B) Pt/TiO<sub>2</sub> composite, and (c) Au/TiO<sub>2</sub> composite. Deconvoluted spectra for (D) Pt<sub>4f</sub> in the Pt/graphene composite, (E) Pt<sub>4f</sub> in the Pt/TiO<sub>2</sub> composite, and (F) Au<sub>4f</sub> in the Au/TiO<sub>2</sub> composite.

**Figure 4: TEM images.** (A) Pt/graphene composite produced by a 1 cm x 50 cm exposure tube (this figure has been modified from Abdolhosseinzadeh et al.<sup>12</sup>. (B) Au/TiO<sub>2</sub>. (C) Pt/TiO<sub>2</sub>. (D) Effect of a high IDE in the formation of large particles and the depletion of its surroundings in Pt/graphene composite. The mean particle sizes for panels A, B, and C are 1.75, 3.8, and 3.77, respectively.

**Figure 5: Concentration changes of the metallic cations during the PD in the developed reactor with various IDEs.** Changes in (A) Pt/graphene, (B) Au/TiO<sub>2</sub>, and (C) Pt/TiO<sub>2</sub>.

**Table 1: Slope values of linear fits to cation concentration changes obtained from ICP-OES analysis.**

## DISCUSSION:

Nanoparticles are the most widely used form of noble-metal-based catalysts. In almost all cases, NNPs are deposited either on a conductive or a semiconductive support material. This hybridization is mostly done by the reduction of the cations of the noble metal in the presence of the intended substrate (material). Hence, a successful synthesis method for the production of NNP-based nanocomposite should meet at least two main requirements: 1) the reduction of the cations should be efficient and complete; 2) the deposition rate, location, and amount should be controllable. In this work, we have demonstrated that the developed reactor (and synthesis method) can successfully address both of the aforementioned requirements.

The XPS survey spectra (**Figure 3**) clearly demonstrated the successful deposition of Pt and Au on RGO and TiO<sub>2</sub> (a conductive and a semiconductive material). Deconvolution of the high-resolution Pt<sub>4f</sub> and Au<sub>4f</sub> peaks revealed no nonmetallic components, which verifies that the photocatalytic reduction method with both PRGO and TiO<sub>2</sub> can completely reduce the Pt<sup>4+</sup> and Au<sup>3+</sup> to Pt<sup>0</sup> and Au<sup>0</sup>, respectively. Considering the deposition yield and required time for it (**Figure 5**), the output of this method is comparable with (or even better than) most of the conventional

NNP deposition methods (i.e., polyol method<sup>18</sup>).

As mentioned earlier, since photoexcited electrons (produced by the substrate itself) reduce the metal cations in a PD reaction, NNPs only form on the substrate, which allows researchers to control the deposition location (not everywhere in the suspension). Furthermore, thanks to the unique pulsed excitation of the substrate (photocatalyst), both nucleation and growth can be controlled. This is mainly due to the fact that, by limiting the exposure time (and/or UV light intensity), a very small and controlled amount of photoexcited electrons are produced in a specific location on the substrate. These electrons have a short lifetime and, due to the poor conductivity of the photocatalyst (semiconductor), cannot move too far from the location that was generated there. Hence, in order to form a stable nucleus which should possess a minimum radius, a specific number of electrons should be generated in one excitation pulse (exposure). This implies that a minimum IDE (exposure length and/or UV light intensity) was required to initiate the PD in the reactor, which can explain the unsuccessful Pt deposition on PRGO with the 5 cm x 0.4 cm exposure tube (**Figure 5A**, negligible concentration changes). Similar behavior was observed when using very low IDEs for TiO<sub>2</sub>-based composites (corresponding data are not provided here). This is mainly due to the fact that the critical IDE value for the formation of stable nuclei is directly related to the quantum yield (since it is usually hard to measure the absolute quantum yield, apparent quantum yield can also be used<sup>19</sup>) of the photocatalyst material (0.36%–0.41% for PRGO and 0.97%–1.1% for TiO<sub>2</sub>).

When the number of photoexcited electrons (per exposure) are larger than the value needed for a stable nucleus formation, as shown in **Figure 5** and **Table 1**, the photodeposition rate (monitored by ICP-OES) has a linear relation with the exposure time and UV light intensity. Even when comparing the Au/TiO<sub>2</sub> and Pt/TiO<sub>2</sub> systems, since Pt<sup>4+</sup> needs one more electron than Au<sup>3+</sup>, the photodeposition rate is higher (1.46) for Au/TiO<sub>2</sub> (the expected ratio is  $4/3 = 1.33$ ). It should be mentioned here that in some cases, the obtained PD rate ratios have slight differences with the expected values (especially for Pt), which is probably due to the fact that the proposed simple model for the nucleation and growth in the PD systems presented here is not completely valid in multi-electron reductions, and other parameters should also be taken into account. At the final stages of the PD in all the systems (**Figure 5**), an abrupt change in the deposition rate has happened, which implies that a significant change in the deposition process has occurred. This is due to the fact that in the proposed model, it was assumed (but not specifically stated) that for each photogenerated electron, a metallic cation will be available immediately to consume it, which is apparently not the case when concentrations of the metal cations fall below a specific value (the diffusion of the cations should also be taken into account).

Since this deviation from the linear behavior occurs in low concentrations, where the major part of the cations is deposited, and the deposition of the remaining cations will require much more time, it is reasonable to conduct the PD in the linear region and recover the remaining cations from the solution by the well-developed hydrometallurgical extraction methods<sup>20</sup>. In this case, the developed reactor can operate in a continuous manner and the desired product can be collected (taken out of the reactor) after a known period of circulation. It is also possible that, by increasing the reactor length, by using either multiple parallel tubes or spring-like tubes, the

precursors can enter the reactor from one side and the products can exit from the other side.

Considering the aforementioned discussions, it is clear that by minimizing the IDE (but keeping it higher than the critical value needed for the formation of the nuclei), researchers can get small monodisperse particles with a uniform distribution, but the production time will also increase significantly. For instance, as also shown in **Figure 6**, the time required for obtaining the same amount of Pt loading in the Pt/graphene system when using the 5 cm x 2 cm and 1 cm x 50 cm tubes is approximately five times longer (in the linear region). On the other hand, by increasing the IDE (either the exposure length or the UV light intensity), growth will dominate the nucleation (similar to the conventional PD methods) and large particles will form. In very high IDEs, as described earlier, a formed particle may suck the electrons from its vicinity (since it has a better conductivity) and disfavor the formation of other nuclei around it. In this case, the particle grows enormously, and the particle size distribution of the final product will be very wide (**Figure 4D**). This phenomenon is more problematic in high quantum-yield photocatalysts (comparing TiO<sub>2</sub> with PRGO), and proper IDE adjustment is more challenging. As a result, shorter exposure lengths and a lower illumination dose (number of the UV lamps) are used for TiO<sub>2</sub>-based composites and still, as can be seen in TEM images, the graphene-based composite has a better monodispersity than the two other TiO<sub>2</sub>-based composites. Hence, the IDE should be carefully optimized to get the highest quality product with the highest yield. The results and discussions presented here clearly demonstrate the potential and abilities of the developed reactor for a precisely controlled synthesis of NNP-based catalysts (on both types of substrates) on a large scale and in a continuous manner.

#### ACKNOWLEDGMENTS:

The authors would like to thank Sabanci University and Swiss Federal Laboratories for Materials Science and Technology (Empa) for all the support provided.

#### DISCLOSURES:

The authors have nothing to disclose.

#### REFERENCES

1. Okitsu, K., Mizukoshi, Y. Catalytic Applications of Noble Metal Nanoparticles Produced by Sonochemical Reduction of Noble Metal Ions. In *Handbook of Ultrasonics and Sonochemistry*. Edited by Ashokkumar, M., 325–363, Springer. Singapore (2016).
2. Shakoory Oskooie, M., Menciloglu, Y. Z., Unal, S., Hayat Soytaş, S. Rapid Microwave-assisted Synthesis of Platinum Nanoparticles Immobilized in Electrospun Carbon Nanofibers for Electrochemical Catalysis. *ACS Applied Nano Materials*. doi:10.1021/acsanm.8b01395 (2018).
3. Kaplan, B. Y. et al. (*Invited*) Graphene: A Promising Catalyst Support for Oxygen Reduction Reaction in Polymer Electrolyte Membrane Fuel Cells. *ECS Meeting Abstracts*. MA2018-01, 2300 (2018).
4. Iliev, V., Tomova, D., Bilyarska, L., Eliyas, A., Petrov, L. Photocatalytic properties of TiO<sub>2</sub> modified with platinum and silver nanoparticles in the degradation of oxalic acid in aqueous solution. *Applied Catalysis B: Environmental*. **63**, 266–271 (2006).
5. Bumajdad, A., Madkour, M. Understanding the superior photocatalytic activity of noble metals

- modified titania under UV and visible light irradiation. *Physical Chemistry Chemical Physics*. **16**, 7146 (2014).
6. Şanlı, L. I., Bayram, V., Yazar, B., Ghobadi, S., Gürsel, S. A. Development of graphene supported platinum nanoparticles for polymer electrolyte membrane fuel cells: Effect of support type and impregnation–reduction methods. *International Journal of Hydrogen Energy*. **41**, 3414–3427 (2016).
7. Işikel Şanlı, L., Bayram, V., Ghobadi, S., Düzen, N., Alkan Gürsel, S. Engineered catalyst layer design with graphene-carbon black hybrid supports for enhanced platinum utilization in PEM fuel cell. *International Journal of Hydrogen Energy*. **42**, 1085–1092 (2017).
8. Domínguez-Domínguez, S., Arias-Pardilla, J., Berenguer-Murcia, Á., Morallón, E., Cazorla-Amorós, D. Electrochemical deposition of platinum nanoparticles on different carbon supports and conducting polymers. *Journal of Applied Electrochemistry*. **38**, 259–268 (2008).
9. Pan, X., Xu, Y.-J. Defect-Mediated Growth of Noble-Metal (Ag, Pt, and Pd) Nanoparticles on TiO<sub>2</sub> with Oxygen Vacancies for Photocatalytic Redox Reactions under Visible Light. *The Journal of Physical Chemistry C*. **117**, 17996–18005 (2013).
10. Zhang, Y., Zhang, N., Tang, Z.-R., Xu, Y.-J. Graphene Oxide as a Surfactant and Support for In-Situ Synthesis of Au–Pd Nanoalloys with Improved Visible Light Photocatalytic Activity. *The Journal of Physical Chemistry C*. **118**, 5299–5308 (2014).
11. Abdolhosseinzadeh, S., Asgharzadeh, H., Sadighikia, S., Khataee, A. UV-assisted synthesis of reduced graphene oxide–ZnO nanorod composites immobilized on Zn foil with enhanced photocatalytic performance. *Research on Chemical Intermediates*. **42**, 4479–4496 (2016).
12. Abdolhosseinzadeh, S., Sadighikia, S., Alkan Gürsel, S. Scalable Synthesis of Sub-Nanosized Platinum-Reduced Graphene Oxide Composite by an Ultraprecise Photocatalytic Method. *ACS Sustainable Chemistry & Engineering*. **6**, 3773–3782 (2018).
13. Zhang, N., Yang, M.-Q., Liu, S., Sun, Y., Xu, Y.-J. Waltzing with the Versatile Platform of Graphene to Synthesize Composite Photocatalysts. *Chemical Reviews*. **115**, 10307–10377 (2015).
14. Han, C., Zhang, N., Xu, Y.-J. Structural diversity of graphene materials and their multifarious roles in heterogeneous photocatalysis. *Nano Today*. **11**, 351–372 (2016).
15. Abdolhosseinzadeh, S. *Bandgap Modulation of Graphene Oxide and Its Application in the Photocatalytic Deposition of Metallic Nanoparticles*. Doctoral dissertation. Sabanci University (2017).
16. Abdolhosseinzadeh, S. et al. Fast and fully-scalable synthesis of reduced graphene oxide. *Scientific Reports*. **5**, 10160 (2015).
17. Ma, Y., Wei, X. Determination of platinum in waste platinum-loaded carbon catalyst samples using microwave-assisted sample digestion and ICP-OES. *AIP Conference Proceedings* **1829** (1), 020008 (2017).
18. Sevilla, M., Sanchís, C., Valdés-Solís, T., Morallón, E., Fuertes, A. B. Highly dispersed platinum nanoparticles on carbon nanocoils and their electrocatalytic performance for fuel cell reactions. *Electrochimica Acta*. **54**, 2234–2238 (2009).
19. de Sá, D. S. et al. Intensification of photocatalytic degradation of organic dyes and phenol by scale-up and numbering-up of meso- and microfluidic TiO<sub>2</sub> reactors for wastewater treatment. *Journal of Photochemistry and Photobiology A: Chemistry*. **364**, 59–75 (2018).
20. Kononova, O. N., Leyman, T. A., Melnikov, A. M., Kashirin, D. M., Tselukovskaya, M. M. Ion exchange recovery of platinum from chloride solutions. *Hydrometallurgy*. **100**, 161–167 (2010).



Figure 1

[Click here to access/download;Figure;1.psd](#)





Figure 2





Figure 3

[Click here to access/download;Figure;Figure 3.psd](#)






Figure 5




Table 1

| System                     | Pt/graphene | Pt/graphene | Pt/graphene | Au/TiO2 | Au/TiO2  |
|----------------------------|-------------|-------------|-------------|---------|----------|
| Condition                  | 5 x 0.4 cm  | 5 x 2 cm    | 1 x 50 cm   | 2 lamps | 4 lamps  |
| Slope in the linear region | ~0          | -0.00932    | -0.04412    | -0.066  | -0.12179 |

|                     |                     |
|---------------------|---------------------|
| Pt/TiO <sub>2</sub> | Pt/TiO <sub>2</sub> |
| 2 lamps             | 4 lamps             |
| -0.05112            | -0.08332            |

| Name of Material/ Equipment                   | Company                   |
|---|---------------------------|
| Chloroplatinic acid solution                  | Sigma Aldrich             |
| Hydrogen tetrachloroaurate(III) hydrate       | Alfa Aesar                |
| TiO2 Nanopowder (TiO2, anatase, 99.9%, 100nm) | US research nanomaterials |
| Graphite flakes                               | Sigma Aldrich             |
| Sulfuric acid                                 | Sigma Aldrich             |
| Hydrogen peroxide                             | Sigma Aldrich             |
| L-Ascorbic acid                               | Sigma Aldrich             |
| Hydrochloric acid                             | Sigma Aldrich             |
| Sodium hydroxide                              | Sigma Aldrich             |
| Potassium permanganate                        | Merck                     |
| Corning® Silicone Septa for GL45 Screw Cap    | Sigma Aldrich (Corning)   |
| Polyvinyl chloride pipe                       | Koctas                    |
| Fuded silica (Quartz) tube                    | Technical Glass Products  |
| UV–C lamps                                    | Philips                   |

| Catalog Number            | Comments/Description |
|---------------------------|----------------------|
| 262587-50ML               |                      |
| 12325.03                  |                      |
| US3411                    |                      |
| 332461-2.5KG              |                      |
| 1120802500                |                      |
| H1009-100ML               |                      |
| A92902-500G               |                      |
| 320331-2.5L               |                      |
| S5881-1KG                 |                      |
| 1050821000                |                      |
| CLS139545SS               |                      |
|                           | UV-Reactor casing    |
| TUV PL-L 55W/4P HF 1CT/25 |                      |



| Name of Material/ Equipment                   | Company                   |
|---|---------------------------|
| Chloroplatinic acid solution                  | Sigma Aldrich             |
| Corning Silicone Septa for GL45 Screw Cap     | Sigma Aldrich (Corning)   |
| Fused silica (Quartz) tube                    | Technical Glass Products  |
| Graphite flakes                               | Sigma Aldrich             |
| Hydrochloric acid                             | Sigma Aldrich             |
| Hydrogen peroxide                             | Sigma Aldrich             |
| Hydrogen tetrachloroaurate(III) hydrate       | Alfa Aesar                |
| L-Ascorbic acid                               | Sigma Aldrich             |
| Polyvinyl chloride pipe                       | Koctas                    |
| Potassium permanganate                        | Merck                     |
| Sodium hydroxide                              | Sigma Aldrich             |
| Sulfuric acid                                 | Sigma Aldrich             |
| TiO2 Nanopowder (TiO2, anatase, 99.9%, 100nm) | US research nanomaterials |
| UV–C lamps                                    | Philips                   |

| Catalog Number            | Comments/Description |
|---------------------------|----------------------|
| 262587-50ML               |                      |
| CLS139545SS               |                      |
| 332461-2.5KG              |                      |
| 320331-2.5L               |                      |
| H1009-100ML               |                      |
| 12325.03                  |                      |
| A92902-500G               |                      |
| 1050821000                |                      |
| S5881-1KG                 |                      |
| 1120802500                |                      |
| US3411                    |                      |
| TUV PL-L 55W/4P HF 1CT/25 | UV-Reactor casing    |



1 Alewife Center #200  
Cambridge, MA 02140  
tel. 617.945.9051  
[www.jove.com](http://www.jove.com)

## ARTICLE AND VIDEO LICENSE AGREEMENT

Title of Article:

A Continuous-Flow Photocatalytic Reactor for Precisely-Controlled Deposition of Metallic Nanoparticles

Author(s):

Sina Abdolhosseinzadeh, Mirsajjad Mousavi, Navid Haghmoradi, Selmiye Alkan Gürsel

Item 1 (check one box): The Author elects to have the Materials be made available (as described at

<http://www.jove.com/author>) via: ☒ Standard Access ☐ Open Access

Item 2 (check one box):



The Author is NOT a United States government employee.



The Author is a United States government employee and the Materials were prepared in the course of his or her duties as a United States government employee.



The Author is a United States government employee but the Materials were NOT prepared in the course of his or her duties as a United States government employee.

### ARTICLE AND VIDEO LICENSE AGREEMENT

1. **Defined Terms.** As used in this Article and Video License Agreement, the following terms shall have the following meanings: “**Agreement**” means this Article and Video License Agreement; “**Article**” means the article specified on the last page of this Agreement, including any associated materials such as texts, figures, tables, artwork, abstracts, or summaries contained therein; “**Author**” means the author who is a signatory to this Agreement; “**Collective Work**” means a work, such as a periodical issue, anthology or encyclopedia, in which the Materials in their entirety in unmodified form, along with a number of other contributions, constituting separate and independent works in themselves, are assembled into a collective whole; “**CRC License**” means the Creative Commons Attribution-Non Commercial-No Derivs 3.0 Unported Agreement, the terms and conditions of which can be found at: <http://creativecommons.org/licenses/by-nc-nd/3.0/legalcode>; “**Derivative Work**” means a work based upon the Materials or upon the Materials and other pre-existing works, such as a translation, musical arrangement, dramatization, fictionalization, motion picture version, sound recording, art reproduction, abridgment, condensation, or any other form in which the Materials may be recast, transformed, or adapted; “**Institution**” means the institution, listed on the last page of this Agreement, by which the Author was employed at the time of the creation of the Materials; “**JoVE**” means MyJoVE Corporation, a Massachusetts corporation and the publisher of *The Journal of Visualized Experiments*; “**Materials**” means the Article and / or the Video; “**Parties**” means the Author and JoVE; “**Video**” means any video(s) made by the Author, alone or in conjunction with any other parties, or by JoVE or its affiliates or agents, individually or in collaboration with the Author or any other parties, incorporating all or any portion of the Article, and in which the Author may or may not appear.

2. **Background.** The Author, who is the author of the Article, in order to ensure the dissemination and protection of the Article, desires to have the JoVE publish the Article and create and transmit videos based on the Article. In furtherance of such goals, the Parties desire to memorialize in this Agreement the respective rights of each Party in and to the Article and the Video.

3. **Grant of Rights in Article.** In consideration of JoVE agreeing to publish the Article, the Author hereby grants to JoVE, subject to **Sections 4** and **7** below, the exclusive, royalty-free, perpetual (for the full term of copyright in the Article, including any extensions thereto) license (a) to publish, reproduce, distribute, display and store the Article in all forms, formats and media whether now known or hereafter developed (including without limitation in print, digital and electronic form) throughout the world, (b) to translate the Article into other languages, create adaptations, summaries or extracts of the Article or other Derivative Works (including, without limitation, the Video) or Collective Works based on all or any portion of the Article and exercise all of the rights set forth in (a) above in such translations, adaptations, summaries, extracts, Derivative Works or Collective Works and (c) to license others to do any or all of the above. The foregoing rights may be exercised in all media and formats, whether now known or hereafter devised, and include the right to make such modifications as are technically necessary to exercise the rights in other media and formats. If the “Open Access” box has been checked in **Item 1** above, JoVE and the Author hereby grant to the public all such rights in the Article as provided in, but subject to all limitations and requirements set forth in, the CRC License.

## ARTICLE AND VIDEO LICENSE AGREEMENT

4. Retention of Rights in Article. Notwithstanding the exclusive license granted to JoVE in **Section 3** above, the Author shall, with respect to the Article, retain the non-exclusive right to use all or part of the Article for the non-commercial purpose of giving lectures, presentations or teaching classes, and to post a copy of the Article on the Institution's website or the Author's personal website, in each case provided that a link to the Article on the JoVE website is provided and notice of JoVE's copyright in the Article is included. All non-copyright intellectual property rights in and to the Article, such as patent rights, shall remain with the Author.

5. Grant of Rights in Video – Standard Access. This **Section 5** applies if the "Standard Access" box has been checked in **Item 1** above or if no box has been checked in **Item 1** above. In consideration of JoVE agreeing to produce, display or otherwise assist with the Video, the Author hereby acknowledges and agrees that, Subject to **Section 7** below, JoVE is and shall be the sole and exclusive owner of all rights of any nature, including, without limitation, all copyrights, in and to the Video. To the extent that, by law, the Author is deemed, now or at any time in the future, to have any rights of any nature in or to the Video, the Author hereby disclaims all such rights and transfers all such rights to JoVE.

6. Grant of Rights in Video – Open Access. This **Section 6** applies only if the "Open Access" box has been checked in **Item 1** above. In consideration of JoVE agreeing to produce, display or otherwise assist with the Video, the Author hereby grants to JoVE, subject to **Section 7** below, the exclusive, royalty-free, perpetual (for the full term of copyright in the Article, including any extensions thereto) license (a) to publish, reproduce, distribute, display and store the Video in all forms, formats and media whether now known or hereafter developed (including without limitation in print, digital and electronic form) throughout the world, (b) to translate the Video into other languages, create adaptations, summaries or extracts of the Video or other Derivative Works or Collective Works based on all or any portion of the Video and exercise all of the rights set forth in (a) above in such translations, adaptations, summaries, extracts, Derivative Works or Collective Works and (c) to license others to do any or all of the above. The foregoing rights may be exercised in all media and formats, whether now known or hereafter devised, and include the right to make such modifications as are technically necessary to exercise the rights in other media and formats. For any Video to which this Section 6 is applicable, JoVE and the Author hereby grant to the public all such rights in the Video as provided in, but subject to all limitations and requirements set forth in, the CRC License.

7. Government Employees. If the Author is a United States government employee and the Article was prepared in the course of his or her duties as a United States government employee, as indicated in **Item 2** above, and any of the licenses or grants granted by the Author hereunder exceed the scope of the 17 U.S.C. 403, then the rights granted hereunder shall be limited to the maximum rights permitted under such

statute. In such case, all provisions contained herein that are not in conflict with such statute shall remain in full force and effect, and all provisions contained herein that do so conflict shall be deemed to be amended so as to provide to JoVE the maximum rights permissible within such statute.

8. Protection of the Work. The Author(s) authorize JoVE to take steps in the Author(s) name and on their behalf if JoVE believes some third party could be infringing or might infringe the copyright of either the Author's Article and/or Video.

9. Likeness, Privacy, Personality. The Author hereby grants JoVE the right to use the Author's name, voice, likeness, picture, photograph, image, biography and performance in any way, commercial or otherwise, in connection with the Materials and the sale, promotion and distribution thereof. The Author hereby waives any and all rights he or she may have, relating to his or her appearance in the Video or otherwise relating to the Materials, under all applicable privacy, likeness, personality or similar laws.

10. Author Warranties. The Author represents and warrants that the Article is original, that it has not been published, that the copyright interest is owned by the Author (or, if more than one author is listed at the beginning of this Agreement, by such authors collectively) and has not been assigned, licensed, or otherwise transferred to any other party. The Author represents and warrants that the author(s) listed at the top of this Agreement are the only authors of the Materials. If more than one author is listed at the top of this Agreement and if any such author has not entered into a separate Article and Video License Agreement with JoVE relating to the Materials, the Author represents and warrants that the Author has been authorized by each of the other such authors to execute this Agreement on his or her behalf and to bind him or her with respect to the terms of this Agreement as if each of them had been a party hereto as an Author. The Author warrants that the use, reproduction, distribution, public or private performance or display, and/or modification of all or any portion of the Materials does not and will not violate, infringe and/or misappropriate the patent, trademark, intellectual property or other rights of any third party. The Author represents and warrants that it has and will continue to comply with all government, institutional and other regulations, including, without limitation all institutional, laboratory, hospital, ethical, human and animal treatment, privacy, and all other rules, regulations, laws, procedures or guidelines, applicable to the Materials, and that all research involving human and animal subjects has been approved by the Author's relevant institutional review board.

11. JoVE Discretion. If the Author requests the assistance of JoVE in producing the Video in the Author's facility, the Author shall ensure that the presence of JoVE employees, agents or independent contractors is in accordance with the relevant regulations of the Author's institution. If more than one author is listed at the beginning of this Agreement, JoVE may, in its sole discretion, elect not take any action with respect to the Article until such time as it has received complete, executed Article and Video License Agreements from each such author. JoVE reserves the right, in its absolute and sole discretion and without giving any reason therefore, to accept or decline any work submitted to JoVE. JoVE and its employees, agents and independent contractors shall have

## ARTICLE AND VIDEO LICENSE AGREEMENT

full, unfettered access to the facilities of the Author or of the Author's institution as necessary to make the Video, whether actually published or not. JoVE has sole discretion as to the method of making and publishing the Materials, including, without limitation, to all decisions regarding editing, lighting, filming, timing of publication, if any, length, quality, content and the like.

11. **Indemnification.** The Author agrees to indemnify JoVE and/or its successors and assigns from and against any and all claims, costs, and expenses, including attorney's fees, arising out of any breach of any warranty or other representations contained herein. The Author further agrees to indemnify and hold harmless JoVE from and against any and all claims, costs, and expenses, including attorney's fees, resulting from the breach by the Author of any representation or warranty contained herein or from allegations or instances of violation of intellectual property rights, damage to the Author's or the Author's institution's facilities, fraud, libel, defamation, research, equipment, experiments, property damage, personal injury, violations of institutional, laboratory, hospital, ethical, human and animal treatment, privacy or other rules, regulations, laws, procedures or guidelines, liabilities and other losses or damages related in any way to the submission of work to JoVE, making of videos by JoVE, or publication in JoVE or elsewhere by JoVE. The Author shall be responsible for, and shall hold JoVE harmless from, damages caused by lack of sterilization, lack of cleanliness or by contamination due to the making of a video by JoVE its employees, agents or independent contractors. All sterilization, cleanliness or decontamination procedures shall be solely the responsibility of the Author and shall be undertaken at the Author's

expense. All indemnifications provided herein shall include JoVE's attorney's fees and costs related to said losses or damages. Such indemnification and holding harmless shall include such losses or damages incurred by, or in connection with, acts or omissions of JoVE, its employees, agents or independent contractors.

12. **Fees.** To cover the cost incurred for publication, JoVE must receive payment before production and publication the Materials. Payment is due in 21 days of invoice. Should the Materials not be published due to an editorial or production decision, these funds will be returned to the Author. Withdrawal by the Author of any submitted Materials after final peer review approval will result in a US\$1,200 fee to cover pre-production expenses incurred by JoVE. If payment is not received by the completion of filming, production and publication of the Materials will be suspended until payment is received.

13. **Transfer, Governing Law.** This Agreement may be assigned by JoVE and shall inure to the benefits of any of JoVE's successors and assignees. This Agreement shall be governed and construed by the internal laws of the Commonwealth of Massachusetts without giving effect to any conflict of law provision thereunder. This Agreement may be executed in counterparts, each of which shall be deemed an original, but all of which together shall be deemed to be one and the same agreement. A signed copy of this Agreement delivered by facsimile, e-mail or other means of electronic transmission shall be deemed to have the same legal effect as delivery of an original signed copy of this Agreement.

A signed copy of this document must be sent with all new submissions. Only one Agreement required per submission.

### CORRESPONDING AUTHOR:

Name:

Selmiye Alkan Gürsel

Department:

Faculty of Engineering and Natural Sciences

Institution:

Sabanci University

Article Title:

A Continuous-Flow Photocatalytic Reactor for Precisely-Controlled Deposition of Metallic Nanoparticles

Signature:



Date:

July 31, 2018

Please submit a signed and dated copy of this license by one of the following three methods:

- 1) Upload a scanned copy of the document as a pdf on the JoVE submission site;
- 2) Fax the document to +1.866.381.2236;
- 3) Mail the document to JoVE / Attn: JoVE Editorial / 1 Alewife Center #200 / Cambridge, MA 02139

For questions, please email [submissions@jove.com](mailto:submissions@jove.com) or call +1.617.945.9051

Dear Dr. Steindel,

We truly appreciate your kind efforts for reviewing and evaluating our manuscript. Your constructive and valuable comments have been implemented in the submitted revised manuscript. We have done our best to address all your concerns, but any additional improvement or correction will be appreciated as well.

Thank you for your kind attention,

Best regards,

Selmiye Alkan Gursel

Professor of Materials Science and Engineering,  
Faculty of Engineering and Natural Sciences  
Sabanci University,  
Istanbul, 34956, Turkey  
Tel: +902164839573  
Fax: +902164839550  
Email: selmiye@sabanciuniv.edu

---

**1. 1: Some more details on the reactor setup should be added; e.g., how exactly are T1 and T2 attached to the bottle? How exactly is the quartz tube fixed inside the illumination tube? Please also include materials used here in the Table of Materials.**

Previous sentences were revised, and more accurate descriptions were added from line 127 to 128 and 154 to 155. Table of Materials was updated.

---

**2. 3.1.2/3.2.1: What exactly are the gas flows in these steps?**

The following sentence was added from line 270 to 275.

*"The N<sub>2</sub> gas flow has no effect on the synthesis process itself and hence, has no specific value. However, it is continuously applied to maintain a positive pressure inside the system and avoid O<sub>2</sub> penetartion. Bubble formation at endpoint of the T<sub>1</sub> tube inside the water filled Erlenmeyer is the only requirement for the flow adjustment."*

---

**3. Please include explicit permission for Figures used from a previous publication. Explicit permission can be expressed in the form of a letter from the editor or a link to the editorial policy that allows re-prints. Please upload this information as a .doc or .docx file to your Editorial Manager account.**

This has been requested several times from ACS publications but unfortunately **no** response has been received. We are not aware of the normal time frame for the issuance

of these types of permission but will appreciate if you allow us to obtain it before the publication of the current work.

---

**4. Figure 2: Please explain V0, T1, etc. in the Figure legend.**

Corresponding explanations were added to the figure legend.

---

**5. Figure 4: Please explain the distributions in the Figure legend. Also, do you have a distribution for 4d?**

Corresponding explanations were added to the figure legend. Figure 4d is provided as an undesirable synthesis condition and hence including particle distribution curves does not seem to be very appropriate.

---

**6. Figure 5: Please explain how the lines were fit and how well they fit (e.g., R-squared; possibly in Table 1 instead).**

Corresponding fitting data were added to the manuscript from line 350 to 357.