


	1	2	3	4	5	6	7	8	9	10	11	12
A	0.665	0.271	0.538	0.529	0.507	0.482	0.373	0.385	0.394	0.249	0.245	0.253
B	0.740	0.285	0.553	0.553	0.518	0.477	0.361	0.376	0.401	0.251	0.241	0.245
C	0.553	0.261	0.445	0.511	0.492	0.491	0.396	0.410	0.312	0.264	0.256	0.259
D	0.558	0.272	0.453	0.520	0.499	0.479	0.389	0.407	0.307	0.262	0.264	0.263
E	0.410	0.244	0.497	0.467	0.453	0.482	0.368	0.388	0.432	0.239	0.249	0.257
F	0.408	0.249	0.502	0.459	0.456	0.476	0.382	0.364	0.428	0.242	0.244	0.245
G	0.313	0.231	0.474	0.511	0.518	0.447	0.302	0.352	0.369	0.248	0.242	0.248
H	0.307	0.227	0.481	0.520	0.513	0.493	0.304	0.347	0.358	0.257	0.254	0.239



NGF loading sol. conc. (µg/ml)	NGF mass in loading sol. (µg)	NGF collected post-loading sol. conc. (µg/ml)	NGF mass in collected post-loading sol. (µg)	NGF mass loaded (µg)	NGF mass loaded per cm ² (µg/cm ²)	NGF loading efficacy (%)
58.48 ± 4.68	3.04 ± 0.24	5.59 ± 0.96	0.28 ± 0.05	2.76 ± 0.25	4.31 ± 0.39	91 ± 11